

Open-Cage Fullerene-like Graphitic Carbons as Catalysts for Oxidative Dehydrogenation of Isobutane [*J. Am. Chem. Soc.* **2009**, *131*, 7735–7741].
Chengdu Liang,* Hong Xie, Viviane Schwartz,*
Jane Howe, Sheng Dai, and Steven H. Overbury

Page 7736, section 2.1.2. The quantities of F127 and phloroglucinol in the synthesis procedure were inadvertently transposed. The text should read: “In a typical preparation, F127 (25.2 g), phloroglucinol (12.6 g), and hydrochloric acid 37 wt % aqueous solution (5 g) were dissolved in 650 mL of absolute ethanol.” This error does not affect the conclusions in the paper.

JA9083557

10.1021/ja9083557

Published on Web 10/28/2009