Combining Furan Annulation, Heck Reaction, and Sonogashira Coupling for the Synthesis of Oligoaryls

ORGANIC LETTERS

2002 Vol. 4, No. 24 4305–4307

Ching-Yuan Liu[†] and Tien-Yau Luh*,^{†,‡}

Department of Chemistry, National Taiwan University, Taipei, Taiwan 106, and Institute of Chemistry, Academia Sinica, Taipei, Taiwan 115

tyluh@chem.sinica.edu.tw

Received September 21, 2002

ABSTRACT

A variety of benzene—furan—alkene/alkyne conjugated oligomers of precise length and constitution were synthesized iteratively by combining furan annulation, Heck reaction, and Sonogashira coupling.

Oligoaryls and their vinylene or acetylene homologues of desired conjugation length have been widely investigated because of their potential optoelectronic applications. There has been extensive uses of heteroaromatic rings such as thiophene in these applications. Interestingly, studies on furan derivatives for these applications have been rare. The recently reported a convenient one-pot synthesis of symmetric oligoaryls 2 containing two furan moieties (eq 1).6.7 These oligoaryls are thermally stable and exhibit bright fluorescence in the blue light region. It is noteworthy that 2a has been shown to be a highly efficient non-amine-based

hole-transporting material in electroluminescent devices.⁷ The basic synthetic strategy shown in eq 1 involves the reaction of a thiolato-substituted allenyl anion 3, generated in situ from 1 and BuLi, with a dialdehyde followed by the acid-catalyzed ring closure. Since both vinyl and alkynyl substituents are stable under the reaction conditions,⁶ it is envisaged that substrates containing such functionalities can undergo Heck⁸ and Sonogashira⁹ reactions, respectively, to extend the chain length while incorporating the aldehyde functionality at both ends of the oligoaryl chain. Further annulation leading to furan rings can then proceed to yield the homologues of oligoaryls. In this paper, we report a bidirectional iterative synthesis of furan-containing oligoaryls by combining furan annulation, Heck reaction, and Sonogashira coupling.

Treatment of 1c with BuLi yielded the corresponding allenyllithium 3b, which was allowed to react with 5a followed by acid treatment, affording 4b in 52% yield. Removal of the TMS group was achieved by treating 4b with K_2CO_3 in methanol—THF to give 4c in 98% yield. In a manner similar to that described in eq 1, reaction of 3a with 6 gave 7 in 45% yield.

[†] National Taiwan University.

[‡] Academia Sinica.

^{(1) (}a) Electronic Materials: The Oligomer Approach; Müllen, K., Wegner, G., Eds. Wiley-VCH: Weinheim, Germany, 1998. (b) Tour, J. M. Acc. Chem. Res. 2000, 33, 791 (c) Bunz, U. F. W. Chem. Rev. 2000, 100, 1605.

⁽²⁾ For a review, see: Gandini, A.; Belgacem, M. N. *Prog. Polym. Sci.* **1997**, 22, 1203 and references therein.

⁽³⁾ Saadeh, H.; Goodson, T., III; Yu, L. *Macromolecules* **1997**, *30*, 4608. (4) (a) Niziurski-Mann, R. E.; Cava, M. P. *Adv. Mater.* **1993**, *5*, 547. (b) Niziurski-Mann, R. E.; Scordillis-Kelley, C.; Liu, T.-L.; Cava M. P.; Carlin, R. T. *J. Am. Chem. Soc.* **1993**, *115*, 887. (c) Hucke A.; Cava, M. P. *J. Org. Chem.* **1998**, *63*, 7413. (d) Politis, J. K.; Nemes J. C.; Curtis, M. D. *J. Am. Chem. Soc.* **2001**, *123*, 2537. (e) Pyo, S. M.; Kim, S. I.; Shim, T. J.; Park H. K.; Ree, M. *Macromolecules* **1998**, *31*, 4777.

⁽⁵⁾ Dufresne, G.; Bouchard, J.; Belletete, M.; Durocher G.; Leclerc, M. *Macromolecules* **2000**, *33*, 8252.

⁽⁶⁾ Lee, C.-F.; Yang, L.-M.; Hwu, T.-Y.; Feng, A.-S.; Tseng, J.-C.; Luh, T.-Y. J. Am. Chem. Soc. 2000, 122, 4992.

⁽⁷⁾ Zhang, L.-Z.; Chen, C.-W.; Lee, C.-F.; Wu C.-C.; Luh, T.-Y. Chem. Commun. 2002, 2336.

⁽⁸⁾ de Meijere, A.; Bräse, S. J. Organomet. Chem. 1999, 576, 88.

⁽⁹⁾ Sonogashira, K. In *Metal-Catalyzed Cross-coupling Reactions*; Diederich F., Stang, P. J., Eds. Wiley-VCH: Weiheim, Germany, 1998; pp 203–229.

The presence of double bonds and triple bonds in 7 and 4c, respectively, is essential for the Heck or Sonogashira

Table 1. Photophysical Properties of Oligoaryls

| substrate | λ_{\max} (nm) ^b | $\lambda_{\mathrm{em}} (\mathrm{nm})^b$ | $\Phi_{ m f}$ |
|-----------|------------------------------------|---|---------------|
| 8 | 350, 399 | 508 | 0.45 |
| 9 | 340, 400 | 486 | 0.81 |
| 10 | 397 | 484 | 0.91 |
| 11 | 348, 412 | 507 | 0.64 |
| | | | |

reaction. Thus, treatment of **7** with 4 equiv of **5b** in the presence of 5 mol % Pd(OAc)₂, Ph₃P, and K₂CO₃ under an argon atmosphere for 48 h resulted in the formation of **8** in 75% yield. In a similar manner, the Sonogashira reaction was employed to enable the coupling of **4c** with **5b** in the presence of CuI, Ph₃P, Et₃N, and a catalytic amount of PdCl₂-(PPh₃)₂ in MeCN. Oligoaryl **9** was isolated in 63% yield.

Annulation of **9** with **3a** generated in situ from the reaction of **1d** and BuLi afforded **10** in 38% yield. In a similar manner, reaction of **8** with **3b** gave **11** in 42% yield. Both oligoaryls **10** and **11** have either double bonds or triple bonds at both ends of the conjugated system. Accordingly, further elaboration would be possible by repeating the same procedures leading to higher homologues of oligoaryls, which can be used as molecular wires. Although the yields of the annulation are moderate, compounds **8**–**11** were easily precipitated by the addition of methanol to the CH₂Cl₂ solutions of the crude products.

The photophysical properties of **8**–**11** were briefly examined, and the results are summarized in Table 1. These oligoaryls exhibited a bluish green emission in CHCl₃ solution with high quantum efficiency. Compound **11** was somewhat unstable, with slow decomposition observed when the CHCl₃ solution was exposed to ambient light. As

11

illustrated in Table 1, the conjugation lengths in **8–11** already reached saturation and essentially the λ_{max} values for each of these oligoaryls remained similar.

In summary, we have demonstrated a new convenient route by combining furan annulation and Heck and Sonogashira reactions for the synthesis of a variety of benzene—furan—alkene/alkyne conjugated oligomers of precise length (up to 6 nm) and constitution. Further extension by using this iterative strategy will be feasible leading to the synthesis of oligoaryls of well-defined conjugation lengths.

Acknowledgment. We thank the Ministry of Education and the National Science Council of the Republic of China for financial support.

Supporting Information Available: Experimental procedures for the preparation of **4b,c** and **8–11**. This material is available free of charge via the Internet at http://pubs.acs.org.

OL026941T

Org. Lett., Vol. 4, No. 24, **2002**