

1	2	3	4
---	---	---	---

Drawing Number
8A1523

The following paint procedure is the Rotork paint procedure for NORSOK M501 SYSTEM 1 RAL7038
(NACE Inspection NOT REQUIRED)

SUBSTRATE MATERIAL :- Ferrous, iron etc.

FINAL COLOUR :- RAL 7038 Agate Grey

TOTAL PAINT THICKNESS :- Minimum : 280 micro metres dft

CLEANING :- Degrease and clean.
All surfaces to be blast cleaned to ISO8501-1 Sa2.5
using aluminium oxide abrasive

PRIMER COAT :- 2 component HS polyamide adduct cured zinc rich epoxy primer

Manufacturer: Sigma

Type: Sigmazinc 109 HS

Min dft: 60 micro metres

BUILD COAT :- 2 component HS zinc phosphate epoxy

Manufacturer: Sigma

Type: Sigmacover 410

Min dft: 170 micro metres

TOP COAT:- 2 component high gloss VOC compliant epoxy acrylic finish

Manufacturer: Sigma

Type: Sigmadur 540

Colour: RAL 7038 Agate Grey

Min dft: 50 micro metres

01	-	-	-	-	10/05/2016	FIRST ISSUE
Iss.	EC	Revised	Checked	Approved	Date	Change Description

AS PART OF CONTINUOUS PRODUCT DEVELOPMENT, ALL DETAILS SUBJECT TO CHANGE WITHOUT PRIOR NOTICE. FOR UP TO DATE DETAILS PLEASE VISIT www.rotork.com

rotork Gears LEEDS - UK www.rotork.com This drawing is confidential and is the property of Rotork Gears and must not be reproduced either wholly or partly. All rights in respect of patents, designs and copyrights are reserved. © 2016	<table border="1" style="width:100%; border-collapse: collapse;"> <tr> <td colspan="2">Document type PAINT</td> <td>Mass</td> </tr> <tr> <td colspan="2" rowspan="2" style="text-align: center;"> </td> <td>Dimensions in mm</td> </tr> <tr> <td>Scale</td> </tr> <tr> <td>Created</td> <td>S BAILEY</td> <td>10/05/2017</td> </tr> <tr> <td>Checked</td> <td>C FLESHER</td> <td>10/05/2017</td> </tr> <tr> <td>Approved</td> <td></td> <td></td> </tr> </table>	Document type PAINT		Mass			Dimensions in mm	Scale	Created	S BAILEY	10/05/2017	Checked	C FLESHER	10/05/2017	Approved			<table border="1" style="width:100%; border-collapse: collapse;"> <tr> <td colspan="2">Title PAINT PROCEDURE. NORSOK M501 SYSTEM 1 RAL7038 AGATE GREY (WITHOUT NACE INSPECTION)</td> </tr> <tr> <td>Drawing Number 8A1523</td> <td>Iss. 01</td> </tr> <tr> <td colspan="2">Sheet 1 of 14 Size A4</td> </tr> </table>	Title PAINT PROCEDURE. NORSOK M501 SYSTEM 1 RAL7038 AGATE GREY (WITHOUT NACE INSPECTION)		Drawing Number 8A1523	Iss. 01	Sheet 1 of 14 Size A4	
Document type PAINT		Mass																						
		Dimensions in mm																						
		Scale																						
Created	S BAILEY	10/05/2017																						
Checked	C FLESHER	10/05/2017																						
Approved																								
Title PAINT PROCEDURE. NORSOK M501 SYSTEM 1 RAL7038 AGATE GREY (WITHOUT NACE INSPECTION)																								
Drawing Number 8A1523	Iss. 01																							
Sheet 1 of 14 Size A4																								

SIGMAZINC 109 HS

Globally
Available

5 pages

October 2012
Revision of July 2011

Description	two component high solids polyamide adduct cured zinc rich epoxy primer
PRINCIPAL CHARACTERISTICS	– designed as a system primer for various paint systems – excellent anticorrosive properties – quick drying, can be overcoated after a short interval – can serve as a holding primer for various maintenance systems for a total repair – very good primer for systems with high solids epoxy buildcoats – complies with SSPC-Paint 20 and ISO 12944.5
COLOURS AND GLOSS	grey, reddish grey – flat
BASIC DATA AT 20 °C	(1 g/cm ³ = 8.35 lb/US gal; 1 m ² /l = 40.7 ft ² /US gal) (data for mixed product)
Mass density	2.8 g/cm ³
Volume solids	66% ± 2%
VOC (Directive 1999/13/EC, SED)	max. 106 g/kg (Directive 1999/13/EC, SED)
VOC (UK PG 6/23(92) appendix 3)	max. 299 g/l (approx. 2.5 lb/gal)
Recommended dry film thickness	60 - 150 µm depending on system
Theoretical spreading rate	11 m ² /l for 60 µm *
Touch dry after	2.5 hours * at 20 °C
Overcoating interval	min. 4 hours *
Full cure after	max. several months *
	7 days at 20 °C
	(data for components)
Shelf life (cool and dry place)	at least 12 months
	* see additional data
RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES	– for immersion exposure: • steel; blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm • steel with approved zinc silicate shop primer; pretreated according to SPSS-Ss – for atmospheric exposure conditions: • steel; blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm • steel with approved zinc silicate shop primer; pretreated according to SPSS or powertool cleaned to SPSS-Pt3 – substrate temperature should be above 5°C and at least 3°C above dew point

SIGMAZINC 109 HS

October 2012

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 80 : 20

- the temperature of the mixed base and hardener should preferably be above 15°C, otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance and slower cure
- thinner should be added after mixing the components

Induction time

none

Pot life

8 hours at 20 °C

AIR SPRAY

Recommended thinner

Thinner 91-92

Volume of thinner

0 - 15%, depending on required thickness and application conditions

Nozzle orifice

1.8 - 2.2 mm

Nozzle pressure

0.3 - 0.6 MPa (= approx. 3 - 6 bar; 44 - 87 p.s.i.)

AIRLESS SPRAY

Recommended thinner

Thinner 91-92

Volume of thinner

0 - 15%, depending on required thickness and application conditions

Nozzle orifice

approx. 0.43 - 0.48 mm (= 0.017 - 0.019 in)

Nozzle pressure

15 MPa (= approx. 150 bar; 2176 p.s.i.)

BRUSH/ROLLER

Recommended thinner

Thinner 91-92

Volume of thinner

0 - 10%

CLEANING SOLVENT

Thinner 90-53

ADDITIONAL DATA

Film thickness and spreading rate

theoretical spreading rate m ² /l	11	8.8	6.6	4.4
dft in µm	60	75	100	150

SIGMAZINC 109 HS

October 2012

Overcoating table for dft 100 µm

substrate temperature	10°C	20°C	30°C	40°C
minimum interval	8 hours	4 hours	3 hours	2 hours
maximum interval	3 months when free from zinc salts and contamination			

- zinc rich primers can form zinc salts on the surface; preferably they should not be weathered for long periods before overcoating
- in clean exterior conditions, a maximum interval of 3 months can be tolerated, but in industrial or marine conditions this interval should be reduced to the practical minimum
- an interval of several months can be allowed under clean interior exposure conditions
- before overcoating visible surface contamination must be removed by high pressure water cleaning, sweep blasting or mechanical cleaning

Curing

Curing table for dft up to 100 µm

substrate temperature	touch dry	dry to handle	full cure
10°C	5 hours	6 hours	20 days
15°C	3 hours	4 hours	10 days
20°C	2.5 hours	3 hours	7 days
30°C	1 hour	1.5 hour	5 days

- SigmaZinc 109 HS can be applied at temperatures between 5°C and 10°C, but the curing rate will be very low
- for such applications alternative zinc rich primers are recommended: SigmaZinc 19, SigmaZinc 158 and SigmaZinc 160 for systems exposed to atmospheric conditions, SigmaGuard 750 for systems exposed to immersed conditions
- adequate ventilation must be maintained during application and curing (please refer to sheets 1433 and 1434)

Worldwide availability

Whilst it is always the aim of Sigma Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances.

Under these circumstances an alternative product data sheet is used.

SIGMAZINC 109 HS

October 2012

REFERENCES

Safety indications	see information sheet 1430
Safe working in confined spaces	see information sheet 1433
Cleaning of steel and removal of rust	see information sheet 1490
Explanation to product data sheets	see information sheet 1411
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Directives for ventilation practice	see information sheet 1434
Conversion labels	see information sheet 1410
Specification for mineral abrasives	see information sheet 1491
Relative humidity - substrate temperature - air temperature	see information sheet 1650

SAFETY PRECAUTIONS

- for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets
- this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

SIGMAZINC 109 HS

October 2012

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

284209	PDS	7701
	grey	5000001800
218766	reddish grey	5010001800

SIGMACOVER 410

Globally
Available

4 pages

August 2012
Revision of August 2011**Description**

two component high solids, high build, polyamide cured epoxy coating

PRINCIPAL CHARACTERISTICS

- general purpose epoxy build coat in protective coating systems for steel and concrete structures exposed to atmospheric land or marine conditions
- excellent durability
- can be recoated with various two component and conventional coatings even after long weathering periods
- easy application by airless spray
- available in MIO or conventional pigmented grade

COLOURS AND GLOSS

MIO and a selected range of colours – flat

BASIC DATA AT 20 °C(1 g/cm³ = 8.35 lb/US gal; 1 m²/l = 40.7 ft²/US gal)

(data for mixed product)

Mass density

1.9 g/cm³ (MIO), 1.5 g/cm³ (conventional pigmented grade)

Volume solids

80% ± 2%

VOC (Directive 1999/13/EC, SED)

max. 126 g/kg (Directive 1999/13/EC, SED)

VOC (UK PG 6/23(92) appendix 3)

max. 240 g/l (approx. 2.0 lb/gal)

(UK PG 6/23(92) Appendix 3)

Recommended dry film thickness

75 - 200 µm depending on system

Theoretical spreading rate

10.7 m²/l for 75 µm *

Touch dry after

3 hours * at 20 °C

Overcoating interval

min. 10 hours *

max. 6 months *

Full cure after

7 days * at 20 °C

(data for components)

Shelf life (cool and dry place)

at least 12 months

* see additional data

**RECOMMENDED
SUBSTRATE CONDITIONS
AND TEMPERATURES**

- previous suitable primer; dry and free from any contamination and zinc salts, and sufficiently roughened if necessary
- when applied to zinc silicate, a mist coat and full coat technique is required
- substrate temperature should be at least 5°C and at least 3°C above dew point during application and curing

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 80 : 20

- the temperature of the mixed base and hardener should preferably be above 15°C, otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance and slower cure
- thinner should be added after mixing the components

Induction time

none

SIGMACOVER 410

August 2012

Pot life 6 hours at 20 °C *
* see additional data

AIRLESS SPRAY

Recommended thinner Thinner 91-92
Volume of thinner 0 - 10%, 30 - 40% when mist coat applied
Nozzle orifice approx. 0.45 - 0.53 mm (= 0.018 - 0.021 in)
Nozzle pressure 20 - 25 MPa (= 200 - 250 bar; 2901 - 3626 p.s.i.)

BRUSH/ROLLER

Recommended thinner Thinner 91-92
Volume of thinner 0 - 5%
Application by brush may show brush marking, due to the thixotropic nature of the paint and is most suitable to small areas, tight angle areas or for stripe coating or touch up.
Application by roller will leave roller marking and is suitable for minimum dft requirements only.
A roller suitable for epoxy application only must be used.

CLEANING SOLVENT

— Thinner 90-53

ADDITIONAL DATA**Film thickness and spreading rate**

theoretical spreading rate m ² /l	10.7	5.3	4
dft in µm	75	150	200

Overcoating table for SigmaCover 410 for dft up to 200 µm

substrate temperature	5°C	10°C	20°C	30°C	40°C
minimum interval	36 hours	24 hours	8 hours	6 hours	4 hours

for various two pack epoxy- or polyurethane paint

- * This product has an unlimited maximum overcoating interval provided the surface is free from chalking and other contamination.
- In cases of exposure to direct sunlight or when the surface is contaminated it is recommended that the surface be cleaned and roughened to ensure good adhesion of the subsequent coating.
- The optimum intercoat adhesion is obtained when the subsequent coating is applied before the full cure time of the previous coating has elapsed.

SIGMACOVER 410

August 2012

Curing

Curing table for dft up to 200 µm

substrate temperature	touch dry	dry to handle	full cure
5°C	12 hours	30 hours	20 days
10°C	6 hours	24 hours	14 days
15°C	4 hours	10 hours	10 days
20°C	3 hours	8 hours	7 days
30°C	2 hours	6 hours	5 days
40°C	1.5 hour	4 hours	3 days

- adequate ventilation must be maintained during application and curing (please refer to sheets 1433 and 1434)

Pot life (at application viscosity)

10 °C	12 hours
15 °C	10 hours
20 °C	6 hours
25 °C	4 hours
30 °C	3 hours
40 °C	2 hours

Worldwide availability

Whilst it is always the aim of Sigma Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances.
Under these circumstances an alternative product data sheet is used.

REFERENCES

Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434
Conversion tables	see information sheet 1410
Relative humidity - substrate temperature - air temperature	see information sheet 1650

SAFETY PRECAUTIONS

- for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets
- this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

SIGMACOVER 410

August 2012

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product.

THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG.

Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT.

The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings products are maintained at www.ppgpmc.com.

The English text of this data sheet shall prevail over any translation thereof.

PDS

6823

SIGMADUR 540

Globally
Available

4 pages

November 2012
Revision of December 2010**Description**

two component high gloss VOC compliant epoxy acrylic finish

PRINCIPAL CHARACTERISTICS

- non-isocyanate
- colour and gloss retention superior to standard epoxy coatings
- non-chalking, non-yellowing
- long pot life but quick drying

COLOURS AND GLOSS

wide colour range – highgloss

BASIC DATA AT 20 °C(1 g/cm³ = 8.35 lb/US gal; 1 m²/l = 40.7 ft²/US gal)

(data for mixed product)

Mass density

1.3 g/cm³

Volume solids

54% ± 2%

VOC (Directive 1999/13/EC, SED)

max. 324 g/kg (Directive 1999/13/EC, SED)

VOC (UK PG 6/23(92) appendix 3)

max. 411 g/l (approx. 3.4 lb/gal)

Recommended dry film thickness

50 - 60 µm

Theoretical spreading rate

10.9 m²/l for 50 µm *

Touch dry after

2 hours at 20 °C

Full cure after

7 days at 20 °C

(data for components)

Shelf life (cool and dry place)

at least 12 months

* see additional data

**RECOMMENDED
SUBSTRATE CONDITIONS
AND TEMPERATURES**

- previous epoxy coats; dry and free from any contamination and sufficiently roughened if necessary
- substrate temperature should be above 5°C and at least 3°C above dew point during application and curing

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 90 : 10

- too much solvent results in reduced sag resistance
- the temperature of the mixed base and hardener should preferably be above 15°C, otherwise extra solvent may be required to obtain application viscosity
- if required, thinner should be added after mixing the components

Induction time

none

Pot life

6 hours at 20 °C

SIGMADUR 540

November 2012

AIR SPRAY

Recommended thinner

Volume of thinner

Nozzle orifice

Nozzle pressure

Thinner 91-92

5 - 10%, depending on required thickness and application conditions

1.0 - 1.5 mm

0.3 - 0.4 MPa (= approx. 3 - 4 bar; 44 - 58 p.s.i.)

AIRLESS SPRAY

Recommended thinner

Volume of thinner

Nozzle orifice

Nozzle pressure

Thinner 91-92

0 - 5%, depending on required thickness and application conditions

approx. 0.38 - 0.46 mm (= 0.015 - 0.018 in)

15 MPa (= approx. 150 bar; 2176 p.s.i.)

Sigmadur 540 can be applied to an industrial finish using standard airless spray equipment with recommended pressure and tip sizes. In order to achieve the optimum finish and cosmetic appearance, the product may be thinned by 10% and applied using an air-assisted airless spray gun set up with a smaller tip size (0.011-0.015 in)

BRUSH/ROLLER

Recommended thinner

Volume of thinner

Thinner 91-92

0 - 5%

CLEANING SOLVENT

Thinner 91-92

ADDITIONAL DATA**Film thickness and spreading rate**

theoretical spreading rate m ² /l	10.9	9.1
dft in μ m	50	60

Overcoating table

substrate temperature	5°C	10°C	20°C	30°C
minimum interval	24 hours	16 hours	8 hours	6 hours
maximum interval	no limitation, provided that the surface is free from any contamination			

Curing**Curing table at 50 μ m for SigmaDur 540**

substrate temperature	dry to handle	full cure
5°C	22 hours	14 days
10°C	16 hours	12 days
20°C	10 hours	7 days
30°C	6 hours	4 days

- adequate ventilation must be maintained during application and curing (please refer to sheets 1433 and 1434)

SIGMADUR 540

November 2012

Pot life (at application viscosity)

10 °C	10 hours
20 °C	6 hours
30 °C	3 hours

Worldwide availability

Whilst it is always the aim of Sigma Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances.
Under these circumstances an alternative product data sheet is used.

REFERENCES

Conversion tables	see information sheet 1410
Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Relative humidity - substrate temperature - air temperature	see information sheet 1650

SAFETY PRECAUTIONS

- for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets
- this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes
 - avoid at all times inhalation of aerosol spraymist

SIGMADUR 540

November 2012

WARRANTY

WARRANTY STATEMENT PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer

LIMITATIONS OF LIABILITY

LIMITATION OF LIABILITY IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

204030	PDS white	7740 7000001400
--------	--------------	--------------------