ORION OIL

S-32, MIDC Bhosari, Pune - 411026 Cell : +91 82756 35579
Email : orionoilandgas@gmail.com.Website : www.orionoilandgas.in

---

TECHNICAL DATA SHEET

REV: 1

DATE OF ISSUING : 18.12.2026

PRODUCT : Heavy Bitumen /Asphalt Modifier

Sr.No	Parameter	Test Method	Target Specification	Typical Value
1	Appearance	Visual	Black, Highly Viscous / Solid	Black, Highly Viscous
2	Density at 29.5°C, g/cc	ASTM D-1298	> 0.950	0.985
3	K. Viscosity at 100°C, cSt	ASTM D-445	> 300.0	380.0
4	Softening Point (Ring & Ball) °C	ASTM D-36	+30 to +40	+35
5	Penetration at 25°C, 0.1mm	ASTM D-5	60 - 100	75
6	Ductility at 25°C, cm	ASTM D-113	Min 50	70
7	Solubility in TCE, %	ASTM D-2042	Min 99.0	99.5
8	Flash Point °C (COC)	ASTM D-92	> 250	275

Disclaimer: The values listed in the final column are typical values based on standardized refining performance. We will provide an actual Certificate of Analysis (COA) issued by an independent NABL-accredited facility, along with all other required technical documents, upon dispatch.

Balaji Tavanandi
AUTHORIZED SIGNATORY