

承 认 书

APPROVAL SHEET

客 户

CUSTOMER \_\_\_\_\_

品 名            CC1            型圆片瓷介电容器

ITEM            CC1 Series Ceramic Disc Capacitors

日 期

DATE \_\_\_\_\_

制            造			客            户		
MANUFACTURER			CUSTOMER		
批准 APPROVE	审核 CHECK	拟制 DRAW UP	批准 APPROVE	审核 CHECK	检验 INSPECTION

广东风华高新科技股份有限公司

Fenghua Advanced Technology (Holding)Co. Ltd

## 1.CC1 Type (Class I ) 中低压温度补偿型圆片瓷介电容器:

Low Voltage Temperature Compensated CDC:

(1)、使用范围(Application): 本产品损耗低、容量稳定性高、电容量变化与温度之关系呈预定直线关系。适用于谐振回路和需要补偿温度效应之电路中。

Low DF,stable capacitance,linear capacitance change with temperature change.Applicable to oscillation and temperature compensation circuit.

### (2)、试验环境Test Conditions

a、标准状态(Standard Conditions): 试验环境如无特别规定,以标准试验环境(温度 15℃~35℃,相对湿度 45~75%RH,气压 860~1060mbar)进行试验。

Without other special requirements,Testing will be made at 15℃~35℃ of Temperature , 45~75%RH of Relative Humidity, 860~1060mbar of Air Pressure.

b、基准状态 (Normal Conditions): 测试环境温度 25℃±2℃相对湿度 60~70%RH, 气压 860~1060mbar。

25℃±2℃ of Temperature , 60~70%RH of Relative Humidity, 860~1060mbar of Air Pressure.

## 2、温度系数(表一)(Temperature Characteristics(Table 1))及容量偏差表(表二)(Capacitance Tolerance(Table 2)):


表一 Table 1; (PPM/℃)

材料温度系数及允许偏差 Dielectrics TC&Tolerance	材料 Dielectrics	EIA 代码 EIA Code	JIS、GB 代码 JIS,GB Code	色标 Color
0±60	NP0	C0H	CH	黑色 Black
-33±60	N33	S <sub>1</sub> H	HH	棕色 Brown
-75±60	N75	U <sub>1</sub> H	LH	红色 Red
-150±60	N150	P <sub>2</sub> H	PH	橙色 Orange
-220±60	N220	R <sub>2</sub> H	RH	黄色 Yellow
-330±60	N330	S <sub>2</sub> H	SH	绿色 Green
-470±60	N470	T <sub>2</sub> H	TH	蓝色 Blue
-750±120	N750	U <sub>2</sub> J	UJ or U <sub>2</sub> J	紫色 Purple
+140~-1000	SL	S <sub>2</sub> L	SL or S <sub>2</sub> L	无色标 No color

表二 Table 2:


代码(Tolerance Code)	允许偏差(Tolerance Value)	标称电容量(Standard Capacitance Value)(pF)
C	±0.25 PF	1、2、3、4、5
D	±0.5 PF	3、4、5、6、7、8、9
F	±1 PF	6、7、8、9、10
J	±5%	大于 10pF
K	±10%	
M	±20%	

### 3、我公司常规 I 类低压高频 CC1 型温度特性曲线 TC Chart for CC1




#### 4、产品形状及尺寸 Product Figure&Dimensions

### (1)、散装规格



### (2)、编带规格



单位 Unit : mm

序号 No.	名称(Item)	符号 (Code)	尺寸 (Dimensions)	允差 (Tolerance)	尺寸 (Dimensions)	允差 (Tolerance)
1	本体直径 Body diameter	D	≤11.0	——	>11.0	——
2	本体厚度 Body thickness	T	3.5	max	4.0	max
3	引线直径 Lead diameter	d	0.38-0.50	+0.06/-0.05	0.50-0.65	+0.06/-0.05
4	编带步距 Pitch between capacitors	P	12.7	±1.0	25.4	±1.0
5	输送孔小距 Feed-hole pitch	P <sub>0</sub>	12.7	±0.3	25.4	±0.3
6	输送孔偏距 Feed-hole centre to Lead	P <sub>1</sub>	3.85	±0.4	7.5	±0.8
7	输送孔与芯片中心距 Feed-hole centre to component centre	P <sub>2</sub>	6.35	±1.3	12.7	±1.5
8	引线间距 Lead spacing	见（3）页订购方式第六项“脚距” Specified at How to order in Page 3				
9	本体偏斜 Component alignment	△h	0	±2.0	0	±2.0
10	载带宽度 Tape width	W	18.0	+1.0/-0.5	18.0	+1.0/-0.5
11	粘带宽度 Hold-down tape width	W <sub>0</sub>	10/12	±1.0	13.0	±1.0
12	输送孔高度偏移 Hole position	W <sub>1</sub>	9.0	±0.5	9.0	±0.5
13	粘带页边 Hold-down tape margin	W <sub>2</sub>	3.0	max	3.0	max
14	顶部高度 Height to seating plane	H	20.0**	+1.5/-1.0	20.0**	±1.0
15	引线折弯高度 Height to kink	H <sub>0</sub>	16.0*	±0.5	16.0*	±0.5
16	底部高度 Height to top plane	H <sub>1</sub>	32.25	max	40	max
17	引线末端伸出 Lead end protrusion	l	1.0	max	1.0	max
18	输送孔直径 Feed-hole diameter	D <sub>0</sub>	4.0	±0.2	4.0	±0.2
19	编带总厚度 Total tape thickness	T	0.7	±0.2	0.7	±0.2
20	废品切断高度 Maximum length of snipped lead	L	11.0	max	11.0	max
21	涂装脚漆长 Maximum height of coated lead	e	2.5	max	2.5	max


备注(Remarks):\*\*适用于直引线型(Applicable to straight lead type by marking \*\*)

\*适用于折弯线型 Applicable to kinked lead type by marking \*

## 5、订购方式(How to order):

Rated Voltage Chip Diameter Dielectrics Lead style Lead spacing Capacitance Tolerance Packing style Coating style										
CC <sub>1</sub>	F	7	SL	1	B	331	J	S	P	W
产品 类型 Series Code	额定 电压	片径 直径 ※	材 质	引线 形式	脚 距	容 量	允许 偏差	包装 形式	包封 形式	
CC <sub>1</sub> : 低压温度补偿电容 CC1:low voltage temperature compensation capacitor	D:16V E:25V F:50V H:63V G:100V J:160V K:250V L:500V	Φ 4=4 Φ 5=5 Φ 6=6 Φ 7=7 Φ 8=8 Φ 9=9 Φ 10=10 Φ 11=11	1= Straight lead(23mm)b type 2= Straight lead(17mm)b type 3=Cutting(short lead) 4=straight lead for tape(b type) 5=small kinked inside for tape(a type) 6= Big kinked inside for tape(a type) 7=Double inside kink(c type) 8= Double outside kink(c type) 9= single outside kink(w type)		A:2.5mm+1.0/-0.2 B:5.0mm+0.8/-0.2 D:7.5mm+0.8/-0.2	1R0=1PF 4R7=4.7PF 100=10PF 560=56PF 101=100PF 821=820PF 102=1000PF	C=±0.25PF D=±0.5PF F=±1.00PF J=±5% K=±10% M=±20%	T: Ammo packing S: Bulk	P: Phenol resin	W:代表无铅产品 Lead-Free
			GB code Dielectrics CH NPO HH N33 LH N75 PH N150 RH N220 SH N330 TH N470 UJ N750 SL SL							

figure examples:



4,5,6 for tape same as No.IV specified.

## 6、包装(Packing):

包装之方式将使电容器在运送或保管时不会使电容器受到损伤,并且在包装上适当的地方标明品名料号、数量、批号。Proper packing will prevent capacitors from damage in transportation and storage. Part number,Quantity,Lot number should be expressly indicated in right manner on the packing.

## 7、试验前处理 Treatment before Trial

(1) 前处理: 测定及试验时, 为确保试验结果不致发生疑问, 有必要时应将供试验电容器置于测定温度内 30 分钟以上, 并使之充分的放电。Pre-treatment: Before testing, the capacitors should be remain in conditions of setting temperature 30 minutes at least,and discharged completely,for purpose of achieving right trial results.

(2) 强制干燥: 在试验或测定前, 如有必要预先将供试验电容器干燥, 且无特别规定限制时, 则将电容器放置在温度  $55 \pm 2^{\circ}\text{C}$ , 相对湿度 20%RH 以下  $6 \pm 0.5$  小时干燥之。Compulsive drying: Before testing,the capacitors should be dried.If without special requirements,the capacitors should generally remain  $6 \pm 0.5$  hours in the conditions of temperature of  $55 \pm 2^{\circ}\text{C}$ ,relative humidity of below 20%RH for drying.

## 8、规格及试验方式 Specifications and Testing conditions

项 目 Item	性能 Performance	试验 方法及 条件 Testing methods and conditions
1 、 外观构造 及尺寸 appearance and dimensions	外观无异常、构造及尺寸依图示规定 no visible damage, dimensions measure up	目视 visual inspection
2、静电容量 capacitance	在 规格 范围 内 conform to specifications	测试温度: $25 \pm 2^{\circ}\text{C}$ , 相对湿度 60~70%RH Testing Temperature: $25 \pm 2^{\circ}\text{C}$ ,Humidity: 60~70%RH 测试频率: $1 \pm 0.1\text{MHz}$ , 测试电压: $1 \pm 0.1\text{Vrms}$ , 2 秒内 Testing Frequency: $1 \pm 0.1\text{MHz}$ , Testing voltage: $1 \pm 0.1\text{Vrms}$ , within 2 seconds,
3、损耗角正切 ( $\text{tg } \delta$ ) Dissipation Factor	30PF or up 见 右栏 (show in right column) below 30PF $Q \geq 400+20C$	读数 $\text{tg } \delta$ 值应不大于 0.0015, 60 秒时读数不大于 0.0020 Value of $\text{tg } \delta$ below 0.0015,up to 60 seconds, Value of $\text{tg } \delta$ below 0.0020 测试频率: $1 \pm 0.1\text{kHz}$ , 测试电压: $1 \pm 0.1\text{Vrms}$ , 2 秒内读数 $\text{tg } \delta$ 值应不大于 0.0020, 60 秒时读数不大于 0.0030 Testing Frequency: $1 \pm 0.1\text{MHz}$ , Testing voltage: $1 \pm 0.1\text{Vrms}$ , within 2 seconds, Value of $\text{tg } \delta$ below 0.0020,up to 60 seconds, Value of $\text{tg } \delta$ below 0.0030

项 目 Item		性能 Performance	试验 方法及条件 Testing methods and conditions																		
4、绝缘电阻 (I.R.) Insulation Resistance		I .R≥10,000MΩ	测试电压 testing voltage: 额定电压 rated voltage 施加时间 lasting time:60±5s																		
5、耐电压 (WV)  Withstanding Voltage	端 子 间 between terminals	无不良 no breakdown or damage	测试电压 testing voltage: 额定电压 rated voltage×250% 施加时间 lasting time: 1-5s 充放电流 discharge current: 50mA max																		
	端子与 外装间 between terminal and capacitor	无不良 no breakdown or damage	Metal ball method 测试电压 testing voltage: 额定电压 rated voltage×250% 施加时间 lasting time: 1-5s 充放电流: discharge current: 50mA max																		
6、耐振性 Withstanding vibration	外观 appearance	无异常 No visible damage	频率 Frequency：10-55Hz full swing:1.5mm frequency change: 10Hz-55Hz-10Hz 此试验如无特别规定应 在彼此互相成垂直的方向各操作 2 小时（合计 6 小时）后检查电容器有 无机机械损伤。 If no other special requirements, capacitors will be tested 2 hours on each mutual-vertical direction,total lasting 6 hours.After that,inspect if there is mechanical damage or not.																		
	静电容量 capacitance	在规格范围内 conform to specifications																			
	损耗角正切 DF（tg δ）	在初 期规 格内 conform to previous specifications																			
7、静电容量 温度特性 Static capacitance TC	使用 温度范围 operating temperature range	-25—85℃	<table><tr><td>阶段 step</td><td colspan="2">temperature 温度(℃)</td></tr><tr><td>1</td><td colspan="2">+20±2</td></tr><tr><td>2</td><td colspan="2">最低使用温度±3 Minimum operating temperature±3</td></tr><tr><td>3</td><td colspan="2">+20±2</td></tr><tr><td>4</td><td colspan="2">最高使用温度±3 Maximum operating temperature±3</td></tr><tr><td>5</td><td colspan="2">+20±2</td></tr></table> 最低使用温度Minimum operating temperature：-25℃ 最高使用温度 Maximum operating temperature：+85℃	阶段 step	temperature 温度(℃)		1	+20±2		2	最低使用温度±3 Minimum operating temperature±3		3	+20±2		4	最高使用温度±3 Maximum operating temperature±3		5	+20±2	
	阶段 step	temperature 温度(℃)																			
	1	+20±2																			
2	最低使用温度±3 Minimum operating temperature±3																				
3	+20±2																				
4	最高使用温度±3 Maximum operating temperature±3																				
5	+20±2																				
温度系 数 temperature coefficient	No exceeding of the specifications																				
静电容量温度 变化率 capacitance vs temperature change rate	在±0.2%或±0.05PF 以内， 取较大者为准 Within ± 0.2% or ± 0.05PF,based upon whichever is higher																				
8、端子强度 Termination Adhesion	抗拉强度 pull strength	引线不断裂， 电容器不破损 leads no breakdown,no damage of capacitor	电容器轴方向加重量 Axially apply force																		
	弯 曲 强 度 bending strength		<table><tr><td>线 径 lead diameter (mm)</td><td>荷重 applied force (Kg)</td><td rowspan="2">保 持 时 间 lasting time (S)</td></tr><tr><td>0.31-0.5</td><td>0.5kgf</td></tr><tr><td>0.51 -0.8</td><td>1.0kgf</td><td></td></tr></table>	线 径 lead diameter (mm)	荷重 applied force (Kg)	保 持 时 间 lasting time (S)	0.31-0.5	0.5kgf	0.51 -0.8	1.0kgf											
			线 径 lead diameter (mm)	荷重 applied force (Kg)	保 持 时 间 lasting time (S)																
0.31-0.5	0.5kgf																				
0.51 -0.8	1.0kgf																				
		导线垂直方向加重向下，本体向左 90°、向右 90° 弯曲 试验 2 次。Apply force to lead at lead vertical direction,capacitor body turn 90 ° left, then right,trial 2 times.																			
		<table><tr><td>线径 lead diameter</td><td>荷重 applied force</td></tr><tr><td>0.31-0.5mm</td><td>0.25kG</td></tr><tr><td>0.51-0.8 mm</td><td>0.5 kG</td></tr></table>	线径 lead diameter	荷重 applied force	0.31-0.5mm	0.25kG	0.51-0.8 mm	0.5 kG													
线径 lead diameter	荷重 applied force																				
0.31-0.5mm	0.25kG																				
0.51-0.8 mm	0.5 kG																				

项 目 Item	性能 Performance		试验方法及条件 Testing methods and conditions
9、可焊性 Solderability	导线表面上须有 3/4 以上之面积为焊锡所附著, At least 75% of the lead surface covered by new solder.		前处理 preheating: 沸腾蒸馏水上面放置 1h Above boiling water 1 hour 浸入助焊剂后 After immersing assistant solder, 试验时焊锡温度 Solder temperature: $245 \pm 5^{\circ}\text{C}$ 浸入时间 Duration: $2 \pm 0.5$ 秒 浸入深度 Immersing height: about 1.5-2mm to root 浸渍速度 Immersing speed: $25 \pm 2.5\text{mm/s}$
10、焊锡耐热性 Resistance to solder heat	外观 appearance	无显著之异常 No visible damage	将端子浸入温度为 $350 \pm 10^{\circ}\text{C}$ 的溶锡内,外面保留约 2.0~2.5mm 距离主体边沿,并保持 $3+1/-0$ 秒,取出在常温下放置 4~24 小时后测定之(主体尺寸 $D \leq 5\text{mm}$ ,则用 $270 \pm 5^{\circ}\text{C}$ , 时间 $5 \pm 0.5$ 秒)Immersing terminals into $350 \pm 10^{\circ}\text{C}$ solder, remain 2.0~2.5mm to body outside, after $3+1/-0$ seconds, taking out & placing in normal temperature 4-24 hours, then testing (body diameter below 5mm, applicable to $270 \pm 5^{\circ}\text{C}$ , duration: $5 \pm 0.5$ seconds)
	耐电压 W.V	满足项目 5 conform to item 5 specified	
	静电容量温度变化率 capacitance change rate	在 $\pm 2.5\%$ 或 $\pm 0.25\text{PF}$ 以内,取较大者为准 within $\pm 2.5\%$ or $\pm 0.25\text{PF}$ , based upon whichever is higher	
11、稳态湿热 Moisture & heating stability	外观 appearance	无显著之异常 No visible damage	在温度 $40 \pm 2^{\circ}\text{C}$ , 湿度 90-95%RH 下置 $500+24/-0$ 小时,取出置常温下 1-2 小时后测定之 Remain in $40 \pm 2^{\circ}\text{C}$ of temperature & 90-95%RH of humidity $500+24/-0$ hours, then taking out & placing in normal temperature 1-2 hours, then testing.
	耐电压 W.V	满足项目 5 conform to item 5 specified	
	静电容量温度变化率 capacitance change rate	在 $\pm 5\%$ 或 $\pm 0.5\text{PF}$ 以内,取较大者为准 within $\pm 5\%$ or $\pm 0.5\text{PF}$ , based upon whichever is higher	
	Q 值 Q value	Below 10PF: $Q \geq 200+10\text{C}$ Above 10PF, below 30PF: $Q \geq 275+5\text{C}/2$ 30PF above: $Q \geq 350$	
	绝缘电阻 Insulation Resistance	I.R. $\geq 1,000\text{M}\Omega$	
12、耐湿负荷 Moisture resistance	外观 appearance	无显著之异常 No visible damage	印加额定电压,并在温度 $40 \pm 2^{\circ}\text{C}$ , 湿度 90-95%RH 下置 $500+24/-0$ 小时,取出置常温下 4-24 小时后测定之,充放电电流限于 50mA 以下。Under Rated voltage, $40 \pm 2^{\circ}\text{C}$ of temperature, 90-95%RH of humidity, duration for $500+24/-0$ hours, then taking out & placing in normal temperature 4-24 hours, then testing, maximum charge or discharge current allowed is 50mA
	耐电压 W.V	满足项目 5 Conform to item 5 specified	
	静电容量温度变化率 capacitance change rate	在 $\pm 7.5\%$ 或 $\pm 0.75\text{PF}$ 以内,取较大者为准 within $\pm 7.5\%$ or $\pm 0.75\text{PF}$ , based upon whichever is higher	
	Q 值 Q value	Below 30PF: $Q \geq 100+10\text{C}/3$ Above 30PF: $Q \geq 200$	
	绝缘电阻 Insulation Resistance	I.R. $\geq 500\text{M}\Omega$	



项 目 Item	性能 Performance		试验 方法及条件 Testing methods and conditions
13、高温负荷 High temperature & voltage resistance	外观 appearance	无显著之异常 No visible damage	印加 200%之额定电压,在温度 $85\pm 2^{\circ}\text{C}$ 下置 1000+48/-0 小时,取出置常温下 12-24 小时后测定之,充放电电流限于 50mA 以下。 Under 2 times of Rated voltage, $85\pm 2^{\circ}\text{C}$ of temperature,duration for 1000+48/-0 hours,then taking out& placing in normal temperature 12- 24 hours,then testing,maximum charge or discharge current allowed is 50mA
	耐电压 W.V	满足项目 5 conform to item 5 specified	
	静电容量 温度变化率 capacitance change rate	在 $\pm 3.0\%$ 或 $\pm 0.30\text{PF}$ 以内,取较大者为准 within $\pm 3.0\%$ or $\pm 0.30\text{PF}$ ,based upon whichever is higher	
	Q 值 Q value	Below 10PF: $Q\geq 200+10C$ Above 10PF, below 30PF: $Q\geq 275+5C/2$ Above 30PF: $Q\geq 350$	
	绝缘电阻 Insulation Resistance	$I.R\geq 1, 000M\Omega$	

## 9、标示 Marking

(1)、标示颜色 marking color: 黑色字 black

(2)、温度特性TC: 著色标注 dielectrics color, NPO: 黑色 black, N470:蓝色 blue, N750 : 紫色 purple, SL: 省略不著色 no color

(3)、标称静电容量: 未满 100PF 用实际数字标示, 100PF 以上用三数字代码标示。

Nominal static capacitance: Use the actual capacitance value as code for capacitance below 100PF,and three digital as code for capacitance value above 100PF(including 100PF)

(4)、电容允差: 用记号标示,  $\pm 5\%$  标示 “J”,  $\pm 10\%$  标示 “K”,  $\pm 0.25\text{PF}$  标示 “C”,  $\pm 0.5\text{PF}$  标示 “D”。

Capacitance Tolerance code: J:  $\pm 5\%$ , K:  $\pm 10\%$ , C:  $\pm 0.25\text{PF}$ , D:  $\pm 0.5\text{PF}$

(5)、额定电压: 50V 在标称静电容量的下方加横线, 500V 用黑色数字标示 “500V”。

Rated Voltage:Underline under Nominal static capacitance stands for 50v of voltage. Marking 500v with black digital .

(6)、标示内容: 优先标示容量, 根据需要增加容差、温度特性、电压等标示项目。

Marking content: Frist marking capacitance value, then marking tolerance,TC or voltage etc. as required.