


Specimen 1 to 1



Specimen #
1

	Specimen Type	Jawface Configuration	Tensile stress at Maximum Load [MPa]	Modulus (Chord 0 mm - 0 mm) [GPa]
1	Aluminum 6061	Flat Serrated 16 TPI	89.40722	-----
Mean			89.40722	-----
Standard deviation			-----	-----

	Modulus (Automatic) [GPa]	Tensile stress at Yield (Zero slope) [GPa]
1	28.89718	0.06894
Mean	28.89718	0.06894
Standard deviation	-----	-----