

When measuring alternately in the center and at a distance from the periferi of the slices, a different presentation of the geometric factor is convenient: We write:

$$Q = G \frac{V}{I},$$

$$G = \frac{\pi}{\ln 2} \cdot t \cdot K_3\left(\frac{L}{s}, \frac{d}{s}\right) = \frac{\pi}{\ln 2} \cdot C_0\left(\frac{d}{s}\right) \cdot K_4\left(\frac{L}{s}, \frac{d}{s}\right)$$

where

$\frac{\pi}{\ln 2} \cdot C_0\left(\frac{d}{s}\right) \cdot t$ is the geometric factor when measuring in the center of a circular slice of diameter d and thickness $t < \frac{s}{2}$ (see section I.1), and $K_4\left(\frac{L}{s}, \frac{d}{s}\right)$ is the additional correction to apply when measuring at a distance L from the periferi of the slice.

$K_4\left(\frac{L}{s}, \frac{d}{s}\right)$ is tabulated below and plotted at page 52.