

DTF Pressing Matrix

● SUB CAMP 2026 · NINJA TRANSFERS

Every fabric. Every cover sheet. One page.

FABRIC	NO SILICONE COVER	WITH SILICONE COVER
Cotton (light or dark)	310°F · 15s · Med-High	330°F · 15s · Med-High
50/50 blends, triblends	300°F · 12s · Med	320°F · 12s · Med
Polyester, jerseys, mesh	290°F · 12s · Med + pillow	310°F · 12s · Med + pillow
Denim, canvas, heavy	320°F · 15s · Firm	340°F · 15s · Firm
Hoodies (multi-layer)	310°F · 17s · Med-High + pillow	330°F · 17s · Med-High + pillow
Hats / structured	320°F top · 130°F bot · 15s + tape	340°F top · 130°F bot · 15s + tape

PILLOW Heat press pillow under seams, zippers, multi-layer goods.

TAPE Thermal heat tape so the transfer can't shift on a curved surface.

PRE-PRESS

3 to 5 seconds before the transfer goes on. Pulls moisture and flattens fibers. Recommended on humid days.

THE SECOND PRESS

After peeling, press again for the same temp, time, and pressure. Cover with parchment. **Don't skip this.** It locks in wash durability.

THE PEEL

Wait at least 5 seconds, peel in one smooth motion. Hot peel is fine. **Glitter, foil, glow = cold peel.**

COVER SHEET RULE OF THUMB

Silicone cover runs hotter than parchment or teflon. Bump temp +20°F when using it. Wait 24 hours before the first wash.