
Government College of Engineering Kannur

Sound Absorption Measurement in Impedence Tube (ISO 10534 - 2)

Inspection Report No:		Date :	11/ 7/2024
Material Type :		**Testing Conditions**	
Density kg/m³ :		Temperature˚C :	
Thickness :		Humidity %:	



Thickness		25 mm
Sample		1
Symbol in graph		
Imp tube/Rev.		Imp
100	Hz	16
125	Hz	10
160	Hz	4
200	Hz	1
250	Hz	1
315	Hz	2
400	Hz	4
500	Hz	24
630	Hz	3
800	Hz	5
1000	Hz	4
1250	Hz	8
1600	Hz	12
2000	Hz	20
2500	Hz	25
3150	Hz	36
4000	Hz	63
5000	Hz	33
6300	Hz	18
NRC (Normal)		12.2
NRC (Random)		0


Tested By : GOVT. COLLEGE OF ENGINEERING KANNUR

Note : Random NRC Value is Approximate calculated value.

Government College of Engineering Kannur

Sound Absorption Measurement in Impedence Tube (ISO 10534 - 2)

Inspection Report No:		Date :	11/ 7/2024
Material Type :		**Testing Conditions**	
Density kg/m³ :		Temperature˚C :	
Thickness :		Humidity %:	



Thickness		10 mm
Sample		1
Symbol in graph		
Imp tube/Rev.		Imp
100	Hz	18
125	Hz	12
160	Hz	6
200	Hz	2
250	Hz	2
315	Hz	2
400	Hz	3
500	Hz	29
630	Hz	2
800	Hz	4
1000	Hz	3
1250	Hz	5
1600	Hz	8
2000	Hz	23
2500	Hz	25
3150	Hz	36
4000	Hz	73
5000	Hz	33
6300	Hz	19
NRC (Normal)		14.2
NRC (Random)		0


Tested By : GOVT. COLLEGE OF ENGINEERING KANNUR

Note : Random NRC Value is Approximate calculated value.

Government College of Engineering Kannur

Sound Absorption Measurement in Impedence Tube (ISO 10534 - 2)

Inspection Report No:		Date :	11/ 7/2024
Material Type :		**Testing Conditions**	
Density kg/m³ :		Temperature˚C :	
Thickness :		Humidity %:	



Thickness		10 mm
Sample		1
Symbol in graph		
Imp tube/Rev.		Imp
100	Hz	18
125	Hz	11
160	Hz	5
200	Hz	2
250	Hz	1
315	Hz	1
400	Hz	2
500	Hz	31
630	Hz	1
800	Hz	3
1000	Hz	3
1250	Hz	5
1600	Hz	9
2000	Hz	1
2500	Hz	40
3150	Hz	18
4000	Hz	22
5000	Hz	98
6300	Hz	26
NRC (Normal)		9
NRC (Random)		0

Tested By : GOVT. COLLEGE OF ENGINEERING KANNUR

Note : Random NRC Value is Approximate calculated value.