

NATIONAL INSTITUTE OF SCIENCE EDUCATION AND
RESEARCH

SIXTH SEMESTER PROJECT REPORT

**Study on spin current in a NM/HM
bilayer**

Author:
Ashish PANIGRAHI

Supervisor:
Dr. Kartik SENAPATI

*A report submitted in fulfillment of the requirements
for the course of P398*

in the

Superconducting Spintronics Lab
School of Physical Sciences

June 25, 2021

Declaration of Authorship

I, Ashish PANIGRAHI, declare that this thesis titled, “Study on spin current in a NM/HM bilayer” and the work presented in it are my own. I confirm that:

- This work was done wholly or mainly while in candidature as part of the coursework for sixth semester at this University.
- Where I have consulted the published work of others, this is always clearly attributed.
- Where I have quoted from the work of others, the source is always given. With the exception of such quotations, this thesis is entirely my own work.
- I have acknowledged all main sources of help.
- Where the thesis is based on work done by myself jointly with others, I have made clear exactly what was done by others and what I have contributed myself.

Date: June 25, 2021

NATIONAL INSTITUTE OF SCIENCE EDUCATION AND RESEARCH

Abstract

Dr. Kartik Senapati

School of Physical Sciences

P398

Study on spin current in a NM/HM bilayer

by Ashish PANIGRAHI

This is your abstract.

Acknowledgement

I would like to take this opportunity to thank my supervisor, Dr. Kartik Senapati, for supervising me for my sixth semester project. His guidance and positivity have helped maintain my morale throughout my work.

I would also like to especially thank my collaborator, Mr. Tapas Ranjan Senapati, who guided me in working with the instruments and made sure that I understood the relevant concepts required for the project.

Contents

Abstract	ii
Acknowledgement	iii
1 Introduction	1
1.1 Why is spin current so important?	1
2 The Hall effects	2
2.1 Introduction - Ordinary Hall effect	2
2.1.1 Mechanism of OHE	3
2.1.2 Hall coefficient	4
Calculating the Hall coefficient	4
2.2 Anomalous Hall effect (AHE)	5
2.2.1 Mechanism of AHE	6
2.3 Spin Hall effect (SHE)	7
2.3.1 Spin Current	7
Mathematical analysis	8
2.4 Inverse Spin Hall effect (ISHE)	9
3 A semiclassical approach to SHE	10
3.1 SHE revisited: relation with AHE	10
3.2 Mechanisms behind the phenomena	10

3.2.1	Extrinsic: Skew-scattering	11
3.2.2	Extrinsic: Side-jump	11
3.2.3	Intrinsic	11
4	Methodology	12
4.1	Experimental plan	12
4.2	Preparation of sample	12
4.2.1	Photolithography	13
4.2.2	Magnetron sputtering	13
5	Results of the experiment	14
6	Limitations & future prospects	15

List of Figures

2.1	Schematic diagram of the Hall effect <i>Image credit: Ashcroft & Mermin, Solid State Physics</i>	2
2.2	A more "self-explanatory" diagram of the Hall effect <i>Image credit: C.M Hurd, The Hall effect in metals and alloys</i>	3
2.3	Schematic behaviour of the Hall resistivity ρ_H as a function of magnetic induction B in a metal showing appreciable magnetization. <i>Image credit: C.M Hurd, The Hall effect in metals and alloys.</i> . . .	6
2.4	The total sum of rate of all charge variations across a surface is equal to the total current entering the surface. <i>Image credit: "Spin Current", Ken-ichi Uchida and Eiji Saitoh</i>	8
2.5	Comparison between SHE and ISHE. <i>Image credit: M.B Jungfleisch, PhD Thesis</i>	9
4.1	Side view of the trilayer sample	13
4.2	Patterned Cu/Pt sample	13

List of Abbreviations

OHE	Ordinary Hall Effect
AHE	Anomalous Hall Effect
SHE	Spin Hall Effect
ISHE	Inverse Spin Hall Effect
NM	Normal Metal
HM	Heavy Metal
SOC	Spin Orbit Coupling

Chapter 1

Introduction

1.1 Why is spin current so important?

Spin current is a crucial part of the field of spintronics. Pure spin current refers to the flow of a net angular momentum where there is no measurable charge current (the type of current that we can measure using ammeters).

Chapter 2

The Hall effects

2.1 Introduction - Ordinary Hall effect

These effects originally deal with the application of an external magnetic field on a current carrying material and subsequently observing the effect either on the conductor or the electric current itself.

In 1879, Edwin Hall was exploring this interaction and tried to determine the effect of the magnetic field on a current carrying wire, with a suspicion that it either affected the whole length of the wire or only the moving electrons.

He later devised a rather simple experiment based on the argument that “if the current of electricity in a fixed conductor is itself attracted by a magnet, the current should be drawn to one side of the wire, and therefore the resistance experienced should be increased.” [1]

Hall couldn't detect this extra resistance (which we now know as magnetoresistance) but concluded that a transverse force in the opposite direction must exist and which appears as a transverse voltage across the width of the conducting material. This is the Hall effect and the transverse voltage is the Hall voltage.

The experiment by Hall is shown in the figure below.




Figure 1.3
Schematic view of Hall's experiment.

FIGURE 2.1: Schematic diagram of the Hall effect
Image credit: Ashcroft & Mermin, *Solid State Physics*




FIGURE 2.2: A more "self-explanatory" diagram of the Hall effect
 Image credit: C.M Hurd, *The Hall effect in metals and alloys*

2.1.1 Mechanism of OHE

In the fig. 2.1 , an electric current is passed along the x direction with corresponding current density is j_x . The cause of this current is an external electric field along the same direction, E_x .

An external magnetic field H along the z direction is applied and the Hall effect is observed.

From the Lorentz force equation

$$\mathbf{F} = q(\mathbf{E} + \mathbf{v} \times \mathbf{H}) \quad (2.1)$$

The second term of the eq. (2.1) is responsible for deflecting the trajectory of the electrons in the negative y -direction and accumulating along the sides of the material. As this accumulation takes place, an electric field builds up along the y -direction which opposes the further deflection of electrons towards the sides. This process continues until an equilibrium is reached, at which this transverse field (or **Hall field**) E_y perfectly balances the Lorentz force and the current flows

only along the longitudinal direction [2].

2.1.2 Hall coefficient

This transverse Hall field E_y can be thought of to be proportional to the external magnetic field H and longitudinal current density j_x . Here, we define the Hall coefficient as

$$R_H = \frac{E_y}{j_x H} \quad (2.2)$$

A rather interesting point to note is that by our construction, j_x and H are along positive x and z directions respectively. E_y however, is along negative y direction, meaning that the resultant sign of the Hall coefficient R_H is negative.

Now, imagine if the charge carriers were positive, this would result in their velocity along x -direction to get reversed (j_x would still be along positive x -direction). The Lorentz force would remain unchanged (as can be seen from eq. (2.1)). Consequentially, the direction of Hall field would be in the opposite direction compared to its direction in the case of negatively charged carriers. This would mean that measuring the Hall coefficient of a material, would help one determine the sign of the charge carriers [2].

Calculating the Hall coefficient

Let us consider current densities j_x and j_y in the presence of an electric field with components E_x and E_y , and in the presence of an external magnetic field H along the z -axis.

The average force per electron is given by the Lorentz force equation, i.e. $\mathbf{F} = -e(\mathbf{E} + \mathbf{v} \times \mathbf{H})$, and hence the average momentum per electron becomes

$$\frac{d\mathbf{p}}{dt} = -e \left(\mathbf{E} + \frac{\mathbf{p}}{m} \times \mathbf{H} \right) - \frac{\mathbf{p}}{\tau} \quad (2.3)$$

During equilibrium, the current becomes time-independent, and hence p_x and p_y satisfy the equations

$$\begin{aligned} 0 &= -eE_x - \omega_c p_y - \frac{p_x}{\tau} \\ 0 &= -eE_y + \omega_c p_x - \frac{p_y}{\tau} \end{aligned} \quad (2.4)$$

where

$$\omega_c = \frac{eH}{m} \quad (2.5)$$

Solving the above equations, we get

$$E_y = - \left(\frac{\omega_c \tau}{\sigma_0} \right) j_x = - \left(\frac{H}{ne} \right) j_x \quad (2.6)$$

This yields the Hall coefficient (eq. (2.2)) to be

$$R_H = -\frac{1}{ne} \quad (2.7)$$

where n is the number density of the charge carriers.

This is a rather astonishing result, suggesting that the Hall coefficient of a material, depends solely on the density of the carriers [2].

We then define Hall resistivity ρ_H as the Hall field E_y per unit longitudinal current density j_x , which is given by

$$\rho_H = \frac{E_H}{j_x} = R_H H \quad (2.8)$$

where the symbols have their usual meanings.

We shall stop our investigation of the Ordinary Hall effect in lieu of the main topic of the report.

2.2 Anomalous Hall effect (AHE)

The previous section dealt with OHE where the nature of the current carrying material is immaterial. Now, we deal with specific characteristics of such material, namely, magnetic metals.

It is observed that when observing Hall effect in such magnetic materials, in addition to OHE, certain unusual phenomena are observed.

In low-field conditions as seen from eq. (2.8), the observed Hall resistivity ρ_H varies linearly with external magnetic field H with the slope given by the Hall coefficient

R_H . For illustration purposes, the example of Hall resistivity ρ_H has been used. The trend is the same for Hall field E_H as can be observed from eq. (2.8).

What about magnetic metals? In such materials, a linear but rapid rise in the Hall field is seen with increasing external magnetic field H . This is followed by a secondary linear rise (with a lower gradient compared to the first), which later saturates at large fields and becomes almost independent of the external field. This is depicted in fig. 2.3




FIGURE 2.3: Schematic behaviour of the Hall resistivity ρ_H as a function of magnetic induction B in a metal showing appreciable magnetization.

Image credit: C.M Hurd, *The Hall effect in metals and alloys*.

In this case, the Hall effect is not simply from the application of Lorentz force on the charge carriers but rather seen as an *anomaly* and is therefore known as the **anomalous Hall effect**.

2.2.1 Mechanism of AHE

It has been shown empirically that this anomalous behaviour can be explained by a superposition of OHE and a strongly temperature dependent term. The curve shown in fig. 2.3 can be empirically fitted by the following equation (in CGS units):

$$\rho_H = R_0 B + \mu_0 R_s M \quad (2.9)$$

where B is the applied magnetic field, R_0 is the ordinary Hall coefficient, M is the magnetization of the material, R_s is the anomalous Hall coefficient and μ_0 is the permeability of free space.

The first term in eq. (2.9) accounts for OHE and is characterized by the more familiar eq. (2.8), whereas the second term is a characteristic of magnetic materials. This magnetization M can be present even without the presence of an external magnetic field B , especially in ferromagnetic materials.

Especially in the case of ferromagnets, R_s is experimentally found to be strongly temperature dependent.

2.3 Spin Hall effect (SHE)

In this type of Hall effect, we generally deal with non-magnetic (or weakly magnetic) materials. For example, a paramagnetic material or a ferromagnetic material beyond its Curie temperature [3]. Strictly speaking, an external magnetic field is not *mandatory* to observed SHE.

When a charge current is supplied in a specific direction along a conducting material, an addition parameter of the charge carriers, namely, the spin of the electrons is responsible for this unique phenomena to take place. For an electrical (charge) current flowing through a sample known to exhibit the phenomena¹, certain scattering mechanisms²preferentially scatter electrons in a direction perpendicular to the flow of charge current, such that electrons with opposite spins get accumulated along the edges of the sample, giving rise to a spin current [4, 3].

In layman terms, SHE reduces to the following: *Spin accumulation at the lateral boundaries of the material, with the directions of spins being opposite at the opposing sides.*

This phenomena is very similar and analogous to OHE, the only difference being that instead of opposite charge accumulation on lateral sides, electrons with opposite spins get accumulated.

We shall discuss the plausible mechanisms responsible for the spin Hall effect in greater detail in the forthcoming chapters.

2.3.1 Spin Current

A pure spin current can be defined as the flow of electrons of spin \uparrow moving in one direction and electrons of the opposite spin i.e. \downarrow electrons moving along the opposite direction. This results in no net charge current (since rate of movement of electrons in opposing directions is the same) and a net flow of angular momentum [5].

¹such samples must have high spin-orbit coupling

Mathematical analysis

From the continuity equation,

$$\nabla \mathbf{J} + \frac{\partial \rho}{\partial t} = 0 \quad (2.10)$$

where \mathbf{J} is the current density and ρ is the charge density.

This eq. (2.10) implies charge conservation law and helps us define the charge current [6].

Analogously, we can define the spin current density \mathbf{J}_s with reference to conservation of spin angular momentum. Considering that spin angular momentum is conserved, we can then define the corresponding continuity equation as

$$\nabla \mathbf{J}_s + \frac{\partial \mathbf{M}}{\partial t} = 0 \quad (2.11)$$

where \mathbf{M} is the magnetization (magnetic moment per unit volume) of the sample. The eq. (2.11) defines the spin current density \mathbf{j}_s [7].




FIGURE 2.4: The total sum of rate of all charge variations across a surface is equal to the total current entering the surface.

Image credit: "Spin Current", Ken-ichi Uchida and Eiji Saitoh

In real solids for most of the cases, the conservation of spin angular momentum is a good approximation. However, in general, the conservation does not hold true due to spin relaxation (due to collisions with impurities in the solid, the spins of the electrons does not remain polarized) [7]. This gives rise to a modified version of eq. (2.11) as:

$$\nabla \mathbf{J}_s + \frac{\partial \mathbf{M}}{\partial t} = -\mathbf{T} \quad (2.12)$$

where T is an indicator of the non-conservation of spin angular momentum (due to spin relaxation and spin generation) [7].

2.4 Inverse Spin Hall effect (ISHE)

In contrast to SHE, the inverse Hall effect is essentially the same but SHE in reverse. When a pure spin current is injected into a material with high SOC (with no charge current), the same scattering mechanisms² as the SHE, allow the spin-polarized electrons to preferentially scatter into opposite directions, leading to a charge imbalance across the edges of the material, thus resulting in a potential difference across the edges (in a tranverse fashion) [8].

The spin \uparrow electrons scatter along one direction and the spin \downarrow electrons scatter along another direction. The surprising aspect about this, is that **both the directions are the same!** This leads to a pure charge current.

The fig. 2.5 is a schematic representation of the phenomena:




FIGURE 2.5: Comparison between SHE and ISHE.

Image credit: M.B Jungfleisch, PhD Thesis

²We shall discuss the plausible mechanisms responsible for the spin Hall effect in greater detail in the forthcoming chapters.

Chapter 3

A semiclassical approach to SHE

In this chapter, we shall look at the semi-classical picture of SHE and try to understand the mechanisms behind the phenomena.

3.1 SHE revisited: relation with AHE

As seen in section 2.1, the OHE results in a charge imbalance along the edges of the conductor in the presence of an external magnetic field. We have also seen that in the case of SHE (sec 2.3), instead of a charge imbalance, we see a spin imbalance i.e. a preferential accumulation along the edges of the material.

Both AHE and SHE are similar in the way that there is a spin imbalance and hence an accumulation of carriers with opposite spins on opposite edges of the sample. The only difference is that in the case of AHE, there is a net magnetization of the material (since we typically use magnetic materials for AHE). This gives preferential scattering of the carriers based on spin but with unequal proportion i.e. due to the net magnetization of the material, the proportion of spin up \uparrow and spin down \downarrow is unequal and hence there will be disproportionate accumulation of one spin (\uparrow or \downarrow) from another (\downarrow or \uparrow).

A significant advantage of SHE over AHE is that the former doesn't require an external magnetic field to function. As long as the material in question possesses a high spin-orbit interaction, SHE is observed and the conversion of pure charge current (unpolarized electrons) gets converted into pure spin current (polarized electrons) with no charge current [3].

3.2 Mechanisms behind the phenomena

Over the past century, the scientific community has agreed upon three plausible mechanisms responsible for SHE. These are categorized into extrinsic and intrinsic mechanisms. Let's dive into the details of the same.

3.2.1 Extrinsic: Skew-scattering

3.2.2 Extrinsic: Side-jump

3.2.3 Intrinsic

Chapter 4

Methodology

In this chapter, we discuss about the techniques and methods used to devise an experiment involving a Pt-Cu bilayer system and subsequently investigate the effect of spin current via SHE.

4.1 Experimental plan

In earlier studies, it has been shown that a pure spin current can be generated and manipulated via a heavy metal through SHE [3, 9, 10]. The detection of this spin current can only be done via conversion into charge current (which is measurable) using ISHE. This generally involves a ferromagnetic layer or a magneto-optical method [11, 12, 13].

In our study, we intend to explore the detection of spin current in a NM/HM bilayer system without a magnetic layer, i.e. via electrical means such as using a simple voltmeter.

In many studies involving the electrical detection of spin current, pure spin current is generated using a ferromagnet, which then gets converted to charge current via ISHE, and is hence, detectable using a voltmeter.

Contrary to the above method, we do not generate pure spin current beforehand, but rather provide a pure charge current as supply to our sample, which is converted to spin current via SHE and is converted back to charge current via ISHE. Keeping this in mind, we design our sample accordingly.

4.2 Preparation of sample

We prepare a trilayer system, using copper (Cu) as the NM and platinum (Pt) as the HM. Here, we sandwich a layer of Cu between two layers of Pt. This is depicted in fig. 4.1.




FIGURE 4.1: Side view of the trilayer sample

Now, as mentioned in section 4.1, we intend to make the shape of our sample to facilitate the conversion of charge to spin current and vice versa. Now, as seen in we see that converted spin current, flows perpendicular to the original charge current and similarly during the back conversion via ISHE. For this, an obvious structural shape would be a path that has two paths, connected via a link being perpendicular to both the paths simultaneously. Hence, a "H"-like structure comes to mind, which is implemented in our experimental setup.

4.2.1 Photolithography




FIGURE 4.2: Patterned Cu/Pt sample

4.2.2 Magnetron sputtering

Through this method, the layer of Cu and Pt are deposited on the SiO₂ wafer at an even thickness, to make the whole sample.

Chapter 5

Results of the experiment

Chapter 6

Limitations & future prospects

Bibliography

- [1] A. S. “On a new Action of the Magnet on Electric Currents1”. In: *Nature* 21.537 (Feb. 1880), pp. 361–361. ISSN: 1476-4687. DOI: 10.1038/021361a0. URL: <https://doi.org/10.1038/021361a0>.
- [2] Neil W Ashcroft, N David Mermin, et al. *Solid state physics*. Vol. 2005. holt, rinehart and winston, new york London, 1976.
- [3] JE Hirsch. “Spin hall effect”. In: *Physical review letters* 83.9 (1999), p. 1834.
- [4] Mikhail I Dyakonov and VI Perel. “Current-induced spin orientation of electrons in semiconductors”. In: *Physics Letters A* 35.6 (1971), pp. 459–460.
- [5] Kannan M Krishnan. *Fundamentals and applications of magnetic materials*. Oxford University Press, 2016.
- [6] John David Jackson. *Classical electrodynamics*. 1999.
- [7] Ken-ichi Uchida and Eiji Saitoh. “Spin Current”. In: *Spintronics for Next Generation Innovative Devices*. John Wiley & Sons, Ltd, Jan. 2016, pp. 43–76. DOI: 10.1002/9781118751886.ch3. URL: <https://doi.org/10.1002/9781118751886.ch3>.
- [8] Mikhail I D’Yakonov and VI Perel. “Possibility of orienting electron spins with current”. In: *Soviet Journal of Experimental and Theoretical Physics Letters* 13 (1971), p. 467.
- [9] Jairo Sinova et al. “Universal intrinsic spin Hall effect”. In: *Physical review letters* 92.12 (2004), p. 126603.
- [10] Shufeng Zhang. “Spin Hall effect in the presence of spin diffusion”. In: *Physical review letters* 85.2 (2000), p. 393.
- [11] T Kimura et al. “Room-temperature reversible spin Hall effect”. In: *Physical review letters* 98.15 (2007), p. 156601.
- [12] Hongwei Li et al. “Spin-orbit torque-induced magnetization switching in epitaxial Au/Fe4N bilayer films”. In: *Applied Physics Letters* 114.9 (2019), p. 092402.
- [13] Christian Stamm et al. “Magneto-optical detection of the spin Hall effect in Pt and W thin films”. In: *Physical review letters* 119.8 (2017), p. 087203.