

PLASTO COLOUR PLUS PVT. LTD.	
D- 42, Opp. Tapadia Polyester, Butibori MIDC Nagpur-441122	
PH: 7722080433	email: kagaplast@gmail.com

CERTIFICATE OF ANALYSIS (PET PREFORMS)

COA NO :1167 /2025-26

Invoice Date : 12-03-2026
 Invoice No. : 1167/ 2025-26
 Customer Name : MAYA INTERNATIONAL EXPORTS
 Quantity (KG) : 500

Description of Preform : 28MM / ALASKA NECK
 Preform Weight : 12.5 gm
 Preform Colour : Clear
 Resin Manufacturer : RELPET
 Resin Grade : 0.80 IV
 Production Date : 10-03-2026
 Test Sample Lot : 5,15,22.

Summary Of Analysis


Sr.No	Test Parameter	Units	Test Equipment	Test Results	Standard
1	Appearance	-	Polariscope	NO Visual Defects	Free of Visual Defect
2	Weight	gm	Digital Scale	12.42	12.5 ± 0.20
3	Preform Height	mm	Digital Height Gauge	83.4	83.1± 0.50
4	Wall Thickness	mm	Preform thickness Gauge	2.11	2.1 ± 0.20
5	Neck Inner Diameter	mm	Digital Vernier caliper	21.67	21.65 ± 0.15
6	Diameter - Neck	mm	Digital Vernier caliper	32.03	32 ± 0.05
7	Resin Intrinsic	dl/g	Supplier Certificate	-	0.80 ± 0.02

This is to certify that the preforms contained in this sale meets and conforms to all requirements called for in International specifications.

This packaging item is made from Food-Grade PET Resin Material.

For PLASTO COLOUR PLUS PVT. LTD.

Authorized Signature
 (Quality In charge)





Reliance Industries Limited

Dahej Manufacturing Division
P.O DAHEJ, TALUKA VAGRA, DIST.BHARUCH, GUJARAT-392130

Registered Office: 3rd Floor, Maker Chambers IV 222, Nariman Point,
Mumbai - 400021, Maharashtra, India.
Quality Control Department – Central Lab

Test Certificate For PET Chips



TC-7460

ULR-TC746025000010402F

Certificate Number	: 890001428808	Date of Testing/Report	: Dec 19, 2025
Plant	: DMD - PET CP 2	Date of Sample/Receipt	: Dec 19, 2025
Product	: G5801 Q	Batch Number	: GN25165352
Product Description	: RELPET G5801 Q	DCPI Date	: Jan 07, 2026
DCPI Number	: 633394000		
Buyer Name	: STATUS POLYMERS,NAGPUR,440018		

Sr. No.	Parameters	Test Method	UOM	Specification	Test Result
01	Intrinsic viscosity	ASTM D 4603	dl/g	0.780 - 0.820	0.790
02	Acetaldehyde	ASTM F 2013	ppm	1.00 Max	0.48
03	Crystallinity	ASTM D 792	%	50.0 Min	53.7
04	b* Colour (CIE)	ASTM D 6290	--	-3.00 - 0.00	-1.49
05	Dust content	ASTM D 7486	ppm	80 Max	69
06	Moisture as packed	ASTM D 6980	%	0.20 Max	0.09

Remarks:-

1. Product conforms to the specification on tested parameters and results relate to the item tested only.
2. Test report shall not be reproduced except in full without approval of the laboratory.
3. Results apply to the sample as received.
4. Test item is analyzed with latest available test methods.
5. This certificate is issued to our internal customer (Production Group).
6. Compliance with BIS norms as per IS 9845-1998 & IS 12252, and US-FDA:177-1630 for Global Migration limit.



Jaiminkumar M Patel

Authorized Signatory
For and on Behalf of
Reliance Industries Limited

This is electronically generated document,hence no signature required.