

GN ALTECH PRIVATE LIMITED

Metoda, Rajkot, Gujarat, India

Hardness Test Report

SAP No.:	PR01CI0459CA	Part No.:	8682-904-00Z
Item:	COVER CASTING	Customer:	Parker Hanifin
Material:	FG-260	Heat Code:	A6A
Heat / Sample:	01	Date:	07-08-2026
Load:	3000 kgf	Ball Diameter:	10 mm

Hardness Specification: 197 - 217

Sr No.	Heat Sample	Diameter	BHN	Result
1	01-01	4.498	207	OK
2	01-02	4.429	206	OK
3	01-03	4.461	203	OK
4	01-04	4.562	202	OK
5	01-05	4.496	207	OK
6	01-06	4.522	209	OK
7	01-07	4.542	209	OK
8	01-08	4.556	210	OK

Average BHN: 206.6 Result: PASS