

GN ALTECH PRIVATE LIMITED


Metoda, Rajkot, Gujarat, India

Tensile Test Certificate

SAP No.:	PR01CI0459CA	Part No.:	8682-904-00Z
Item:	COVER CASTING	Customer:	Parker Hanifin
Material:	FG-260	Heat Code:	A6A
Heat / Sample:	01	Date:	07-08-2026
Machine:	FIE UTE-40	Sample Type:	Round Solid Bar

Results of Tension Test

Maximum Force (Fm)	: 32794.086 N
Max. Displacement	: 22.880 mm
Ultimate Tensile Strength	: 266.402 MPa
Elongation	: N/A %
Yield Stress	: N/A MPa



Displacement (mm)