

GN ALTECH PRIVATE LIMITED


Metoda, Rajkot, Gujarat, India

Tensile Test Certificate

SAP No.:	PR01CI0459CA	Part No.:	8682-904-00Z
Item:	COVER CASTING	Customer:	Parker Hanifin
Material:	FG-260	Heat Code:	A6B
Heat / Sample:	01	Date:	07-08-2026
Machine:	FIE UTE-40	Sample Type:	Round Solid Bar

Results of Tension Test

Maximum Force (Fm)	: 34165.666 N
Max. Displacement	: 26.404 mm
Ultimate Tensile Strength	: 277.544 MPa
Elongation	: N/A %
Yield Stress	: N/A MPa



Displacement (mm)