

GN ALTECH PRIVATE LIMITED

Metoda, Rajkot, Gujarat, India

Hardness Test Report

SAP No.:	PR01CI1632CA	Part No.:	MF012996
Item:	HOUSING CASTING	Customer:	Parker Hanifin
Material:	EN-GJL-300	Heat Code:	C6B
Heat / Sample:	01	Date:	07-08-2026
Load:	3000 kgf	Ball Diameter:	10 mm

Hardness Specification: 187 - 255

Sr No.	Heat Sample	Diameter	BHN	Result
1	01-01	4.587	203	OK
2	01-02	4.468	209	OK
3	01-03	4.436	203	OK
4	01-04	4.571	221	OK
5	01-05	4.433	219	OK
6	01-06	4.534	220	OK
7	01-07	4.536	204	OK
8	01-08	4.584	199	OK

Average BHN: 209.8 Result: PASS