

# GN ALTECH PRIVATE LIMITED


Metoda, Rajkot, Gujarat, India

## Tensile Test Certificate

|                |                 |              |                 |
|----------------|-----------------|--------------|-----------------|
| SAP No.:       | PR01CI1632CA    | Part No.:    | MF012996        |
| Item:          | HOUSING CASTING | Customer:    | Parker Hanifin  |
| Material:      | EN-GJL-300      | Heat Code:   | C6C             |
| Heat / Sample: | 01              | Date:        | 07-08-2026      |
| Machine:       | FIE UTE-40      | Sample Type: | Round Solid Bar |

### Results of Tension Test

|                           |               |
|---------------------------|---------------|
| Maximum Force (Fm)        | : 40907.238 N |
| Max. Displacement         | : 22.909 mm   |
| Ultimate Tensile Strength | : 332.309 MPa |
| Elongation                | : N/A %       |
| Yield Stress              | : N/A MPa     |



Displacement (mm)