

GN ALTECH PRIVATE LIMITED


Metoda, Rajkot, Gujarat, India

Tensile Test Certificate

SAP No.:	PR01CI1632CA	Part No.:	MF012996
Item:	HOUSING CASTING	Customer:	Parker Hanifin
Material:	EN-GJL-300	Heat Code:	C6D
Heat / Sample:	01	Date:	07-08-2026
Machine:	FIE UTE-40	Sample Type:	Round Solid Bar

Results of Tension Test

Maximum Force (Fm)	: 36936.770 N
Max. Displacement	: 23.001 mm
Ultimate Tensile Strength	: 300.055 MPa
Elongation	: N/A %
Yield Stress	: N/A MPa



Displacement (mm)