

GN ALTECH PRIVATE LIMITED

Metoda, Rajkot, Gujarat, India

Hardness Test Report

SAP No.:	RX05SG1849CA	Part No.:	R908107005
Item:	RCS CORPS DE SORTIE BRUT	Customer:	BOSCH REXROTH
Material:	EN-GJS-500-7	Heat Code:	G6E
Heat / Sample:	01	Date:	07-08-2026
Load:	3000 kgf	Ball Diameter:	10 mm

Hardness Specification: 160 - 230

Sr No.	Heat Sample	Diameter	BHN	Result
1	01-01	4.568	186	OK
2	01-02	4.497	200	OK
3	01-03	4.591	193	OK
4	01-04	4.528	188	OK
5	01-05	4.434	211	OK
6	01-06	4.437	213	OK
7	01-07	4.593	179	OK
8	01-08	4.505	208	OK

Average BHN: 197.2 Result: PASS