



AFFINITY PT 1450G1

Polyolefin Plastomer

- Monolayer and coextrusion coating for packaging applications
- Recommended for use with Oriented Polypropylene (OPP as a tie layer or sealant)
- Coextruded with PRIMACOR* polymer as a cost effective foil or PET sealant
- Complies with U.S. FDA
Consult the regulations for complete details. ⁽¹⁾

AFFINITY™ PT 1450G1 Polyolefin Plastomer is produced via INSITE™ Technology. It is an ethylene alpha-olefin resin for monolayer and coextrusion coating that offers excellent low temperature seal initiation, ultimate seal strength, adhesion to (OPP) and good taste and odor performance.

Physical Properties	Test Method	Values ⁽²⁾ English (SI)
Resin Properties		
Melt Index, g/10 min	ASTM D 1238	7.5
Density, g/cc	ASTM D 792	0.9020
DSC Melting Point, °F (°C)	Dow Method	208 (98)
Vicat Softening Point, °F (°C)	ASTM D 1525	171 (77)
Extrusion Coating Performance⁽³⁾		
Seal Initiation Temperature ⁽⁴⁾⁽⁵⁾ , °F (°C)	Dow Method	181 (83)
Adhesion to OPP @ 550°F lb/in.	Dow Method	1.04
@ 600°F lb/in.		0.73
Extrusion Coating Processability		
Recommended Melt Temperature, °F (°C)		550-600 (288-315)
Neck-in @ 600°F and @ 1.0 mil, inches (mm)	Dow Method	5.3 (135)
Minimum Coating Weight, lb/ream (g/m ²)	Dow Method	<4.5 (<7.5)
Minimum Coating Thickness, mil	Dow Method	<0.3

Fabrication Conditions For Extrusion Coating Film:

- Extruder: Black Clawson
- Screw Size: 3.5 in. (90 mm); 30:1 L/D
- Die Gap: 20 mil (0.508 mm)
- Chill Roll Temperature: 57°F (14°C)
- Melt Temperature: 600°F (315°C)
- Output: 250 lb/hr
- Air Gap: 6 in. (150 mm)

- (1) It is the responsibility of the manufacturer of the food contact article to ensure the article is suitable for its intended use. Manufacturers should be aware that foods with a high oil content may compromise the integrity of the packaging.
- (2) Typical values, not to be construed as specifications. Users should confirm results by their own tests.
- (3) 1.0 mil (25µm) coating onto 50 lb Kraft paper.
- (4) Temperature at which 1 lb/in. (4.4 N/25.4 mm) heat seal strength is achieved.
- (5) Heat Seal Strengths, Topware HT Tester, 0.5 S dwell, 40 psi bar pressure, pull speed 150 mm/sec.

Product Stewardship

The Dow Chemical Company and its subsidiaries (Dow) has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours (except, for PELLETHANE™ polyurethane elastomers only, which exceeds 30 days);
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted.

Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful and technically suitable for the intended use. DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; and (3) there is greater potential for Dow to change specifications and/or discontinue production.

Additional Information

North America		Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+32-3-450-2240
	1-989-832-1426		
Mexico:	+1-800-441-4369		
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+60-3-7958-3392

www.dowplastics.com

Published March 2006
©2007 The Dow Chemical Company

