



ELITE™ AT 6900

The Dow Chemical Company - Enhanced Polyethylene Resin

Thursday, November 26, 2020

General Information

Product Description

Main Characteristics:

- HDPE with excellent moisture barrier, low dusting propensity
- Great processability; low back pressure and exceptional bubble stability

Complies with:

- U.S. FDA 21 CFR 177.1520 (c) 2.2
- EU, No 10/2011
- Canadian HPFB No Objection

Consult the regulations for complete details.

General

Material Status	• Commercial: Active
Availability	• North America
Agency Ratings	• EU 10/2011 • FDA 21 CFR 177.1520(c) 2.2 • HPFB (Canada) No Objection
Forms	• Pellets

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.971		ASTM D792
Melt Mass-Flow Rate (190°C/2.16 kg)	1.2	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	2	mil	
Secant Modulus - 2% Secant, MD	158000	psi	ASTM D882
Secant Modulus - 2% Secant, TD	220000	psi	ASTM D882
Elmendorf Tear Strength - MD ²	30	g	ASTM D1922
Elmendorf Tear Strength - TD ²	80	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	273	°F	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	20		ASTM D2457
Haze	44.0	%	ASTM D1003

Processing Information

Extrusion Notes

Fabrication Conditions For Blown Film:

- Screw Size: 3.5 in
- Screw Type: DSB II
- Die Gap: 70 mil (1.7 mm)
- Melt Temperature: 439 °F
- Output: 10.4 lb/hr/in of die circumference
- Die Diameter: 8 in.
- Blow-Up Ratio: 2.5 to 1
- Frost Line Height: 34 in.

ELITE™ AT 6900

The Dow Chemical Company - Enhanced Polyethylene Resin

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method B
