



ELVALOY™ AC 2618

Acrylate Copolymer

Description			
Product Description	ELVALOY™ AC 2618 is a copolymer of ethylene and ethyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process polyethylene type resins.		
Restrictions			
Material Status	Commercial: Active		
Typical Characteristics			
Composition	18% By Weight Ethyl Acrylate comonomer content		
Typical Properties			
Physical	Nominal Values		Test Method(s)
*Density ()	0.93 g/cm³	ASTM D792	ISO 1183
*Melt Flow Rate (190°C/2.16kg)	6 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values		Test Method(s)
*Melting Point(DSC)	95 °C (203 °F)	ASTM D3418	ISO 3146
Vicat Softening Point ()	56 °C (132.8 °F)	ASTM D1525	ISO 306
Processing Information			
*Maximum Processing Temperature	310 °C (590 °F)		
General Processing Information	ELVALOY™ AC 2618 is normally processed at melt temperatures ranging from 235°C - 310°C (455°F - 590°F) in extrusion coating or cast film equipment. A typical extrusion coating extruder temperature profile is given below. Actual processing temperatures will be determined by either the specific equipment or one of the other polymers in a coextrusion. ELVALOY™ AC 2618 can also be used in cast extrusions and coextrusions. It is easily processed on standard equipment used for low density polyethylene.		
Extrusion Coating/Lamination Processing	Nominal Values		
Processing Information	A suggested extrusion set temperature profile		
Feed Zone	185 °C (365 °F)		
Second Zone	235 °C (455 °F)		
Third Zone	260 °C (500 °F)		
Fourth Zone	285 °C (545 °F)		
Fifth Zone	285 °C (545 °F)		
Adapter Zone	285 °C (545 °F)		
Die Zone	285 °C (545 °F)		
FDA Status Information	ELVALOY™ AC 2618 Acrylate Copolymer Resin complies with Food and Drug Administration Regulation 21 CFR 177.1320(a) - - Ethylene-ethyl acrylate copolymer resins, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, except for holding food during cooking, subject to the blend and finished food-contact article meeting the extractive limitations, as shown in paragraph (c)(2) of the Regulation. This resin must be blended with polyethylene or with one or more olefin polymers complying with Food and Drug Administration Regulation 21 CFR 177.1520, or used in a coating complying with 21 CFR 175.300 or 21 CFR 176.170 in such proportions that the ethyl acrylate content of the blend or finished coating does not exceed 8 percent by weight, in accordance with paragraph (b) of 21 CFR 177.1320.		

The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by Dow and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, Dow cannot guarantee or warrant such certifications or information and assumes no liability for their use.

Regulatory Information

For information on regulatory compliance outside of the U.S.A., consult your local Dow representative.

Safety & Handling

For information on appropriate Handling & Storage of this polymeric resin, please refer to the material Safety Data Sheet.

A Product Safety Bulletin, material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your Dow representative.

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- a. long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours (or for PELLETHANE™ Polyurethane Elastomers only, which exceeds 30 days);
- b. use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- c. use as a critical component in medical devices that support or sustain human life; or
- d. use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted.

Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Additional information

North America

U.S. & Canada: **1-800-441-4369**
 1-989-832-1426
Mexico: **+1-800-441-4369**

South Africa **+800-99-5078**

Europe/Middle East

All Countries **+31-11567-2626**
 +800-3694-6367
Italy: **+800-783-825**

Asia Pacific **+800-7776-7776**
 +60-3-7958-5392

Latin America

Argentina: **+54-11-4319-0100**
Brazil: **+55-11-5188-9000**
Colombia: **+57-1-219-6000**
Mexico: **+52-55-5201-4700**

<http://www.dow.com>

Published August 2019

© 2019 The Dow Chemical Company

Version: 130.0

Last modified at 8/6/2019 6:02 AM