

VC710

Ethylene Vinyl Acetate Copolymer

General Information

Description

- ◆ VA Content 33%
- ◆ For Wire & Cable

Applications

- ◆ Wire and cable coating

Properties ¹			
Physical	Test Method	Nominal Values	
Melt Flow Index	ASTM D1238	20.0	g/10min
Density	ASTM D1505	0.958	g/cm ³
Vinyl Acetate Content	LC Method	33	wt.%
Mechanical			
Tensile Stress (Break)	ASTM D638	105	kgf/cm ² 10.3 MPa
Tensile Strain (Break)	ASTM D638	830	%
Thermal			
Melting Point	LC Method	64	°C
VICAT Softening Point	ASTM D1525	<40	°C
Additional Properties			
Hardness (Shore D)	ASTM D2240	24	D scale

NOTE

ISO 9001, 14001, /TS 16949

¹ Properties: these are not to be construed as specifications