



MEHR PETROCHEMICAL COMPANY
TESTING LABORATORY
ISO/IEC 17025 QUALITY MANAGEMENT SYSTEM



Test
TS EN ISO/IEC 17025
AB-0708-T

Doc Name		PRODUCT QUALITY REPORT(F Grade)				Record No.: LAB-686/15
Doc No.		IFQ-FR-029-04				Date: 04/10/2015
HDPE GRADE NO.: 7000F				LOT NO.: 15H105691		
SAMPLE RECEIVING DATE: 03.10.2015				LOT SIZE: 296 Ton (PLANT QUANTITY)		
SAMPLE CHARACTERISTIC/CONDITION: White Pellet				TEST DATE: 03.10.2015		
Cc:		OPERATION MANAGER		MARKETING		
		COO		WARE HOUSE		
		PLANT MANAGER				
TEST ITEM	Unit	REQUIRED RANGE	MEASURED VALUE	UNCERTAINTY	TEST METHOD	
Melt Flow Rate at 190 °C/2.16kg	g/10min	0.030 - 0.050	0.041	± 8.00%	ISO 1133-1	
Density	g/cm ³	0.950 - 0.954	0.954	± 0.23%	ISO 1183-2	
NNI*	-	≥ 100	160	± 6.15%	HZ-F-122-5	
Pellet Appearance*	-	IN RANGE	IN RANGE	-	IFQ-WI-038-00	
LC	-	≥ 75	88	± 0.81%	ASTM E 313	
Particle Size Distribution(Mesh size: 2.50mm)*	% Wt	≥ 95.0	97.2	-	IFQ-WI-037-00	
FAR*	-	≥ -10	+20	-	IFQ-WI-050-00	
OUT PUT*	kg/h	≥ 18.4	21.9	-	IFQ-WI-044-00	
cc:						
The expanded uncertainty is estimated with attention to coverage factor k=2 for normal distribution, providing a level of confidence of approximately 95%.						
* These tests are not under ISO/IEC 17025 scope.						
REMARK:						
CLASS			PRIME			
VERIFIED BY:	A. Mahmoudi			APPROVED BY:	F. Rezaei	
DATE:	Oct 04, 2015			DATE:	Oct 04, 2015	
تهران - خیابان خالد اسلامبولی (وزرا) - خیابان پنجم - طبقه اول - پلاک ۲۲ - کدپستی ۱۵۱۳۶۴۳۹۱۱ ، تلفاکس ۸۸۵۵۴۷۸۵-۸۶ Address: No.22, 5 St, Khaled Eslambouli (Vozara) Ave, Tehran, Iran. Tel Office: +98(21)88554759-80 E-mail: info@mehrpetrochem.com						

