

Provisional Product Data Sheet

SUMITOMO POLYETHYLENE HDPE

F0554

High Density, Blown Film

Applications	For shopping and grocery bags, perforated rolls, trash bags, and industrial liners.
Characteristics	Bimodal blown film grade having high tensile and impact strength, good stiffness and barrier properties with a wide molecular weight distribution for easy processing. Performs well under heavy load conditions.
Typical Processing Conditions	Melt Temperature 180 – 230°C Blow-up Ratio 3 – 5

Typical Properties

Physical		Value	Unit	Method
Melt Index	2.16kg	0.05	g/10min	ASTM D1238
	21.6kg	8	g/10min	ASTM D1238
Density		0.951	g/cm ³	ASTM D792-A
Mechanical		Value	Unit	Method
Shore Hardness-D		67		ASTM D2240
Thermal		Value	Unit	Method
Vicat Softening Temperature	10N	126	°C	ASTM D1525A
Melt Temperature		132	°C	DSC
Brittleness Temperature		< -50	°C	ASTM D746
Film		Value	Unit	Method
Tensile Strength at Break	MD / TD	75 / 50	MPa	ASTM D882
Tensile Elongation at Break	MD / TD	380 / 500	%	ASTM D882
Tensile Modulus, 1% Secant	MD / TD	1050 / 1200	MPa	ASTM D882
Elmendorf Tear Strength	MD / TD	9 / 110	g	ASTM D1922
Dart Drop Impact		240	g	ASTM D1709

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. Actual test results may vary.

Test pieces preparation condition as per ASTM D 4976 and ISO 1872-2.

Film fabrication condition extruder Ø50mm, die Ø120mm, die gap 1.35mm, temperature 200°C, output 50kg/hr, BUR 4, thickness 20µm.

Manufacturer

F0554 is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh).

Food Contact Application

Unmodified F0554 complies with the US FDA Regulation 21 CFR 177.1520 as well as with the EU Directive 2002/72/EC and its amendments for use in direct contact with food. Please contact your nearest SCA representative for more information.

Restriction of Hazardous Substances

The substances regulated under EU Directive 2002/95/EC on RoHS in electrical and electronic equipment are not used in the manufacturing process of F0554 and are therefore not expected to be present.

Storage and Handling

F0554 is supplied in 25kg bags or in bulk containers depending on packaging options available for different markets. It is advisable to store in a well ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odor characteristic of the resin.

Please refer to the Material Safety Data Sheet (MSDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCA prioritizes environmental management in all our operations in responsibility and respect towards the community and the world around us.

Unmodified, our polypropylene and polyethylene products are readily recyclable, both for reuse via reprocessing, and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

Office Locations**SUMITOMO CHEMICAL ASIA PTE LTD**

150 Beach Road #18-05/08 Gateway West SINGAPORE 189720

Phone +65 63035188

Fax +65 62989621

Web Site www.sca.com.sg

SUMITOMO CHEMICAL ASIA PTE LTD

Vietnam Representative Office, 7th Floor, Unit 701-3, Me Linh Point Tower, 2 Ngo Duc Ke Street, Dist. 01, Ho Chi Minh City VIETNAM

Phone +84 8 35202767

Fax +84 8 35202911

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

Unit 46-07 Grand Gateway II, No.3 Hongqiao Road, Xu Hui District, Shanghai CHINA 200030

Phone +86 21 64482255

Fax +86 21 64077365

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

Unit 12E-2 Block C Peace Square, Shenghe Road, Nancheng District, Dongguan, Guangdong CHINA 523071

Phone +86 769 22887316

Fax +86 769 22887885

SCA SOUTH ASIA PETROCHEMICALS PRIVATE LIMITED

Sethi Chambers, Plot No.2, D.D.A. Local Shopping Centre, 2nd Floor, M.O.R. Land, New Rajinder Nagar, New Delhi, INDIA 110060

Phone +91 11 2874 1571

Fax: +91 11 2874 1565

SUMITOMO CHEMICAL EUROPE S.A./N.V.

Woluwelaan, 57, B-1830 Machelen BELGIUM

Phone +32 2 2548799

Fax +32 2 2512991

Web Site www.sumitomo-chem.be

SUMITOMO CHEMICAL EUROPE N.V.

Turkey Liaison Office, Fatih Sultan Mehmet Cad. Yayabeyi Sok. Ilayda Is Mrk, No.12/2, 34810 Kavacik, Beykoz - Istanbul - TURKEY

Phone +90 216 680 3334

Fax: +90 216 680 1012

Disclaimer

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. All information contained in this document is provided in good faith and believed to be reliable on the date compiled. Customer is responsible to ensure that SCA materials, whether used alone or in conjunction with other materials, are suitable for the intended application. SCA accepts no liability whatsoever for any action taken based on this information, and/or for any loss and consequential loss or damage. Please contact your nearest SCA representative for more detailed information.