



HIGH DENSITY POLYETHYLENE



Chandra Asri
Petrochemical

SF5007

Film

CHARACTERISTICS :

- Hexene Copolymer
- High Molecular Weight
- High Impact, Tear, and Tensile Strength
- Good Thin Film processability
- Compliance with FDA Regulation 21 CFR177.1520

APPLICATIONS :

- Blown Film and General Packaging
- Industrial Liner
- Shopping Bags, Disposal Bags and Grocery Bags

Physical Properties	Test Method*	Unit	Value
Density	ASTM D 1505	g/cm ³	0.950
Melt Index (190°C/2.16 kg)	ASTM D 1238	g/10 min.	0.05
Melt Index (190°C/21.6 kg)	ASTM D 1238	g/10 min.	15
Flexural Modulus	ASTM D 790	MPa	1100
Vicat Softening Temperature	ASTM D 746	°C	127
Brittleness Temperature	ASTM D 746	°C	< -70
ECSR [F ₅₀]	ASTM D 1693	Hrs	> 500

Film Properties	@ 20 micron, BUR = 3.8 : 1		
Dart Drop Impact, F ₅₀	ASTM D 1709	g	130
Elmendorf Tear Strength, MD / TD**	ASTM D 1922	kgf/cm	7 / 150
Film Impact Strength	ASTM D 3420	kgf.cm/mm	350
Young's Modulus, MD / TD	ASTM D 882	MPa	850 / 1050
Tensile Strength @ Braek MD / TD	ASTM D 882	MPa	100 / 55
Elongation @ Break MD / TD	ASTM D 882	%	500 / 700

* Polyethylene tested per ASTM D 1928

** MD : Machine Direction TD : Transverse Direction

Conversion : 1 MPa = 10.2 kgf/cm²

1 kJ/m² = 0.01 kgf.cm/mm²

Recommended Processing Conditions :

Melt Temperature 180 - 220 deg. C

Blow-up Ratio 3 -5

This material complies with recommendations and statutory regulations in the USA, Japan and most European countries regarding packaging materials intended to come in contact with foodstuff.

The nominal properties reported herein are typical on the product of CAPC but do not reflect normal testing variance and therefore should not to be construed as specifications.

CAPC reserves the right to make any improvement or amendments to the composition of any grade or product without alteration to the product code.

This document reports accurate and reliable information to the best of our knowledge on the products manufactured by CAPC. Since CAPC can not anticipate or control the conditions under which this information and its product may be used, each user should review the information in the specific context of the intended application. CAPC will not be responsible for damages of any nature resulting from the use of or reliance upon the information.

This technical datasheet is effective as from January 2013 and supersedes all previously published data.

PT. Chandra Asri Petrochemical Tbk

Wisma Barito Pacific Tower A, 7th Floor

Jl. Let. Jend. S. Parman Kav. 62-63

Jakarta 11410, Indonesia

T +6221-530 7950, F +6221-530 8930

www.chandra-asri.com

