



Product Data and Technical Information

Name	Moplen
Grade	EP548S
Resin type	Polypropylene, Impact Copolymer
Description	<i>Moplen</i> EP548S is a nucleated heterophasic copolymer with antistatic agent used for injection moulding applications. It exhibits an outstanding balance of mechanical properties combined with a medium high fluidity. <i>Moplen</i> EP548S is extensively used in housewares and in thin-walled containers for food packaging (e.g. margarine tubs, yoghurt pots, etc.). <i>Moplen</i> EP548S is suitable for food contact.
Availability	Europe, Africa-Middle East
Technical data	
Density	0.9 g/cm ³
Melt flow rate (MFR)	44 g/10 min (230°C/2.16kg)
Melt volume flow rate	59 cm ³ /10min (230°C/2.16kg)
Tensile Modulus	1550 MPa
Tensile Stress at Yield	28 MPa
Tensile Strain at Break	30 %
Tensile Strain at Yield	5 %
Charpy unnotched impact strength	85 kJ/m ² (-20 °C)
Charpy unnotched impact strength	100 kJ/m ² (0 °C)
Charpy unnotched impact strength	110 kJ/m ² (23 °C)
Charpy notched impact strength	3.0 kJ/m ² (-20 °C)
Charpy notched impact strength	3.5 kJ/m ² (0 °C)
Charpy notched impact strength	5.0 kJ/m ² (23 °C)
Heat deflection temperature B (0.45 MPa) Unannealed	95 °C
Ball indentation hardness	68 MPa (H 358/30)
Ductile/Brittle transition temperature	-53 °C
Vicat softening temperature A / 50	151 °C
Vicat softening temperature B / 50	80 °C
Product Data Sheets	 ISO Data Sheet
MSDS (Material Safety Data Sheet)	European  Moplen EP548S