



Product Data and Technical Information

Name	Moplen
Grade	HP462S
Resin type	Polypropylene, Homopolymer
Description	Moplen HP462S is a very narrow Molecular Weight Distribution homopolymer, suitable for extrusion applications. Moplen HP462S is designed for production of continuous filaments. Typical applications are HTY and spunbond nonwoven.
Availability	Asia-Pacific, Australia-NZ, Africa-Middle East
Technical data	
Melt flow rate (MFR)	36 g/10 min
Tensile Modulus	1450 MPa
Tensile Stress at Yield	34 MPa
Tensile Strain at Break	>50 %
Tensile Strain at Yield	8 %
Heat deflection temperature B (0.45 MPa) Unannealed	85 °C
Vicat softening temperature	154 °C (A50 (50°C/h 10N))
Vicat softening temperature	90 °C (B50 (50°C/h 50N))
Product Data Sheets	 ISO Data Sheet
MSDS (Material Safety Data Sheet)	European  Moplen HP462S

Copyright © 2007 Basell Service Company B.V. All rights reserved