



Product Data and Technical Information

Name	Moplen
Grade	HP500N
Resin type	Polypropylene, Homopolymer
Description	<i>Moplen</i> HP500N is a homopolymer used for general purpose injection moulding applications. It exhibits good flow and stiffness. <i>Moplen</i> HP500N is suitable for food contact.
Availability	Europe, Asia-Pacific, Africa-Middle East
Technical data	
Density	0.9 g/cm ³
Melt flow rate (MFR)	12 g/10 min (230°C/2.16kg)
Melt volume flow rate	16 cm ³ /10min (230°C/2.16kg)
Tensile Modulus	1550 MPa
Tensile Stress at Yield	35 MPa
Tensile Strain at Break	>50 %
Tensile Strain at Yield	10 %
Charpy unnotched impact strength	30 kJ/m ² (0 °C)
Charpy unnotched impact strength	110 kJ/m ² (23 °C)
Charpy notched impact strength	3 kJ/m ² (23 °C)
Heat deflection temperature B (0.45 MPa) Unannealed	95 °C
Vicat softening temperature A / 50	153 °C
Vicat softening temperature B / 50	85 °C
Product Data Sheets	 ISO Data Sheet
MSDS (Material Safety Data Sheet)	European  Moplen HP500N

Copyright © 2007 Basell Service Company B.V. All rights reserved