

Provisional Product Data Sheet

SUMITOMO POLYPROPYLENE

FS3011E

Homopolymer, Biaxially Oriented Film

Applications	For print and lamination, adhesive tape, food packaging, cigarette packaging, etc.		
Characteristics	Medium flow BOPP with excellent clarity, gloss and stiffness. Excellent processability and suitable for metallization.		
Typical Processing Conditions	Extrusion Temperature	190 – 250°C	
	Stretching Temperature	130 – 160°C	
	Stretching Ratio MD/TD	4 – 7 / 7 – 10	

Typical Properties

Physical		Value	Unit	Method
Melt Flow Rate	2.16kg	3.0	g/10min	ASTM D1238
Density		0.900	g/cm ³	ASTM D792-A
Mechanical		Value	Unit	Method
Tensile Strength	at Yield	34	MPa	ASTM D638
	at Break	20	MPa	ASTM D638
Tensile Elongation	at Yield	18	%	ASTM D638
	at Break	440	%	ASTM D638
Flexural Modulus		1360	MPa	ASTM D790A
Flexural Strength		35	MPa	ASTM D790A
Izod Impact, 23°C	Notched	3	kJ/m ²	ASTM D256
Rockwell Hardness		96		ASTM D785
Thermal		Value	Unit	Method
Vicat Softening Temperature	10N	151	°C	ASTM D1525A
Melting Temperature		159	°C	DSC
Crystallisation Temperature		118	°C	DSC
Heat Deflection Temperature	0.45MPa	113	°C	ASTM D648
Film		Value	Unit	Method
Tensile Strength at Break	MD / TD	135 / 225	MPa	ASTM D882
Tensile Elongation at Break	MD / TD	100 / 30	%	ASTM D882
Tensile Modulus, 1% Secant	MD / TD	2100 / 3800	MPa	ASTM D882
Haze		0.1	%	ASTM D1003
Gloss	45°	161	%	ASTM D2457

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. Actual test results may vary.

Test pieces preparation condition nozzle temperature 230 °C, mold temperature 60 °C.

Film fabrication condition extrusion temperature 250°C, output 60kg/hr, cast temperature 50°C.

Standard stretching condition MDO stretch ratio 5, temperature 145°C, TDO stretch ratio 8, temperature 157°C, relaxation 6.5%, line speed 25m/min, thickness 20µm.

Food Contact Application

Unmodified FS3011E complies with the US FDA Regulation 21 CFR 177.1520 (c) 1.1a for use in direct contact with food as well as with the EU Directive 2002/72/EC and its amendments 2004/1/EC, 2004/19/EC, 2005/79/EC, and 2007/19/EC.

Restriction of Hazardous Substances

The substances regulated under EU Directive 2002/95/EC on RoHS in electrical and electronic equipment are not used in the manufacturing process of FS3011E and are therefore not expected to be present.

Storage and Handling

FS3011E is supplied in 25kg bags or in bulk containers depending on packaging options available for different markets. It is advisable to store in a well ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odour characteristic of the resin.

Please refer to the Material Safety Data Sheet (MSDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCA prioritizes environmental management in all our operations in responsibility and respect towards the community and the world around us.

Unmodified, our polypropylene and polyethylene products are readily recyclable, both for reuse via reprocessing, and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

Office Locations

SUMITOMO CHEMICAL ASIA PTE LTD
150 Beach Road
#18-05/08 Gateway West
SINGAPORE 189720
Phone +65 63035188
Fax +65 62989621
Web Site www.sca.com.sg

SUMITOMO CHEMICAL ASIA PTE LTD
Shanghai Representative Office
Unit 46-06 Grand Gateway II
No.3 Hongqiao Road
Xu Hui District, Shanghai
CHINA 200030
Phone +86 21 64482255
Fax +86 21 64077365

SUMITOMO CHEMICAL ASIA PTE LTD
Dongguan Representative Office
Unit 12E-1 Block C Peace Square
Shenghe Road, Nancheng District
Dongguan, Guangdong
CHINA 523071
Phone +86 769 22887316
Fax +86 769 22887885

SUMITOMO CHEMICAL INDIA PVT LTD
Moti Mahal, 7th Floor
195, J. Tata Road
Churchgate, Mumbai
400020 INDIA
Phone +91 22 22892610
Fax +91 22 22892600

SUMITOMO CHEMICAL EUROPE S.A./N.V.
Woluwelaan, 57
B-1830 Machelen
BELGIUM
Phone +32 2 2548717
Fax +32 2 2512991
Web Site www.sumitomo-chem.be

Disclaimer

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. All information contained in this document is provided in good faith and believed to be reliable on the date compiled. Customer is responsible to ensure that SCA materials, whether used alone or in conjunction with other materials, are suitable for the intended application. SCA accepts no liability whatsoever for any action taken based on this information, and/or for any loss and consequential loss or damage. Please contact your nearest SCA representative for more detailed information.