



Technical Data Sheet

PP H030 GP/3

Polypropylene homopolymer

DESCRIPTION

PP H030 GP/3 is a polypropylene homopolymer for general purposes. The product is characterized by standard molecular weight distribution, medium melt flow rate, the optimal composition of stability, balanced physical and mechanical properties.

TYPICAL APPLICATIONS

PP H030 GP/3 is used for producing tapes (raffia) and strapping by injection molding, extrusion and thermoforming methods.

Properties		Method	Typical values [*]
Rheology			
Melt Flow Rate	(230 °C/2.16 kg)	ASTM D 1238	3 g/10 min
Mechanical			
Tensile Yield Strength	(50 mm/min)	ASTM D 638	36.3 MPa
Elongation at Yield	(50 mm/min)	ASTM D 638	10%
Elongation at Break	(50 mm/min)	ASTM D 638	>200%
Flexural Modulus	(5 mm/min)	ASTM D 790	1560 MPa

^{*} Typical values; not for specification.

ООО «Tobolsk - Polymer»

Industrial area, Tobolsk, Tyumen region, 626150

Reception:

Tel.: 8(3456) 398-000

Fax: 8(3456) 398 – 077

E-mail: polymer@tpolymer.ru

Website: <http://sibur.com/tpolymer/>

Ltd. «Sibur»

Basic Polymers Division

3-16, Krzhizhanovskogo St., Moscow, 117997

Tel.: 8 (495) 777-55-00

E-mail: servicedbp@sibur.ru