

Product Data Sheet

SUMITOMO POLYPROPYLENE

Y101

Homopolymer, Injection Molding

Applications	For general purpose and houseware applications.
Characteristics	High flow, good heat resistance and high stiffness.
Typical Processing Conditions	Melt temperature : 160 – 240 °C

Typical Properties

Physical		Value	Unit	Method
Melt Flow Rate	230 °C, 2.16 kg	15	g/10min	ASTM D1238
Density		0.9	g/cm ³	ASTM D792-A
Mechanical		Value	Unit	Method
Tensile Strength	at Yield	34	MPa	ASTM D638
	at Break	28	MPa	ASTM D638
Flexural Modulus		1700	MPa	ASTM D790
Izod Impact, Notched	23 °C	2	kJ/m ²	ASTM D256
Rockwell Hardness		105		ASTM D785
Thermal		Value	Unit	Method
Vicat Softening Temperature	10 N	158	°C	ASTM D1525
Heat Deflection Temperature	0.45 MPa	116	°C	ASTM D648
Other		Value	Unit	Method
Shrinkage	MD / TD	1.2 / 1.2		Sumika
Flammability		HB		UL 94

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications; actual test results may vary.
Test specimen preparation conditions : as per ASTM D4101