



CHINA GENERAL PLASTICS CORPORATION

PVC RESIN PROPERTIES

(Grade)	H-61	H-66	H-73	H-80
(k Value)	59-62	65-67	72-74	79-82
Appearance	White Powder	White Powder	White Powder	White Powder
Degree of Polymerization	800+_50	1000+_50	1350+_50	1800+_100
Apparent Density	0.53+_0.03	0.50+_0.03	0.46+_0.03	0.45+_0.05
Specific Gravity	1.4	1.4	1.4	1.4
Particle Size pass through 42 mesh(%)(over)	99.99	99.99	99.99	99.99
Volatile (105°C)(%)(below)	0.3	0.3	0.3	0.3

Applications

Grade	Applications
H-61	Injection Molding (Pipe Fitting), Hollow-vacuum Forming (Bottle Blowing), Rigid Film, Shrinkable Film.
H-66	Flexible and Semi-rigid Product For General Purpose (PVC Film, Sheet, Beach Chair, Venetian Blind, Rigid Pipe, Hose, Low Temperature Wire and Cable Insulation.
H-73	High Impact Flexible Product (PVC leather, Film, Furniture, Shoes), High Impact Sheet, High Voltage Wire and Cable Insulation.
H-80	High Impact, High Flexible, Rubber-like Properties Products (PVC Film, Leather, Extrusion and Injection Compound)