

通用型聚氯乙烯树脂S-1000

Polyvinyl Chloride Resin of General Purpose S-1000

产地 / Product Site：钦州 / Qinzhou

产品介绍 / Overview

S-1000是一种悬浮法聚氯乙烯均聚树脂，白色粉末，具有优良的流动性和加工性能，良好的吸油率，与增塑剂、液体稳定剂等液态助剂相容性良好。

S-1000 is a suspension polyvinyl chloride homopolymer resin, white powder, very good fluidity and fusion properties, very good plasticizer absorption, and very good compatibility with liquid additives, such as plasticizers, stabilizers and so on.

应用领域 / Applications

主要应用于各种硬质、软质聚氯乙烯制品，如下水管材、门窗型材、电线电缆、人造革等。

Mainly areas of application are a variety of rigid and flexible PVC products, such as pipes, door and window profiles, wires, cables, artificial leather, etc.

产品特性 / Product Properties

项 目 Parameter	指 标 / Index		
	优等品 Excellent Grade	一等品 Good Grade	合格品 Qualified Grade
平均聚合度 Average Degree of Polymerization	981-1135		
黏数/(mL/g) 或K值 Viscosity / K-Value	107-118 66-68		
表观密度/(g/mL) ≥	0.48	0.45	0.42
挥发物(包括水)含量/% ≤ Volatiles (Includes Moisture)	0.40	0.40	0.50
100 g树脂增塑剂吸收量/g ≥ Plasticizer Absorption of 100g Resin	22		
残留氯乙烯单体含量/(μg/g) ≤ Residual VCM	5	5	10

项 目 Parameter		指 标 / Index		
		优等品 Excellent Grade	一等品 Good Grade	合格品 Qualified Grade
筛余物/% Sieve Retention R	0.25 mm筛孔 ≤ On 0.25 mm Screen	1.6	2.0	8.0
	0.063 mm筛孔 ≥ On 0.063 mm Screen	97	90	85
“鱼眼”数/(个/400 cm²) Fish-eye Count.		10	20	60
杂质粒子数/个 Number of Impurities		16	30	60
白度(160 ℃, 10 min) /% Whiteness (160 ℃, 10 min)		78	75	70

产品包装 / Package

产品采用PE包装，小包净重25Kg/袋，大包净重1200Kg/袋。

The resin is packaged in PE bags. The net weight of small package is 25Kg per bag and that of large package is 1200Kg per bag.

储运及注意事项 / Storage and Notice

应储存在干燥通风的仓库内，防止日晒和受潮，运输必须用洁净运输工具，防止雨淋和污染。

Resin should be stored in dry and ventilated place to avoid sun and moisture. Clean transportation facilities should be adopted to prevent rain and pollution.