



OCEAN PLASTICS CO., LTD.

5F 310 CHUKWANG ROAD TAIPEI TAIWAN R.O.C.

TEL : 886-2-2306-2131 888-2-2308-1188 EXT 643、645

FAX : 886-2-2302-7471 886-2-2306-2320

Registered trademark :

大洋塑膠粉
YEEVINYL®



POLYVINYL
CHLORIDE RESIN
聚氯乙烯粉

PVC Resin	Properties							Application
	K-Value	Degree of Polymerization	Bulk Density (g/ml)	Volatile Matter (%)	Residual VCM (ppm)	Average Particle Size (μm)	DOP Absorption (ml/g)	
S-101 (SG5)	66±1	1030±50	0.56±0.05	<0.5	<1.0	125±30	>0.20	General rigid sheets and pipe, good for rigid or flexible product
S-103 (SG3)	70±1	1250±50	0.53±0.05	<0.5	<1.0	120±30	>0.25	Insulating materials, vinyl tape, PVC sheets and leather, good for high quality of flexible or semi-rigid product
S-107 (SG8)	57±1	700±50	0.62±0.05	<0.5	<5.0	125±30	>0.10	Blowing bottles, good liquidity for rigid and high transparency product
S-108 (SG7)	60±1	770±50	0.60±0.05	<0.5	<5.0	130±30	>0.15	Vinyl tape, IC tube, good for rigid and high transparency product
S-230 (SG0)	88±2	2250±100	0.43±0.05	<0.5	<5.0	100±30	>0.30	Super-tough grade, for Heat-resistance cable, high tensile strength, weather-resistance, high elastic products.

2003.05.06