



LDPE	LLDPE	MDPE	HDPE	PP	PVC	GPPS	HIPS	EPS	PET	ABS	SBR	PBR	PC	EP
------	-------	------	------	----	-----	------	------	-----	-----	-----	-----	-----	----	----

PVC-S6558

POLYVINYL CHLORIDE

Applications:

Extrusion of flexible sections and hoses: Grade S6558 processed with plasticizer is particularly suitable for the manufacture of rigid sections & hoses. The most varied field of applications satisfied by this product are transparent and solid coloured hoses and sections etc.

Injection moulding : S-PVC in compounds permits a trouble free processing on conventional PVC injection moulding machines for sanitary ware , building parts , water fitting , WC flush tanks etc. Grade S6558 processed without plasticizer is used for the injection moulding.

Storage:

The product should be stored in dry conditions at temperature below 60 °C and protected from UV-light and in such a way that if other materials are on fire , it cannot be decomposed either by flames or hot fumes or heat radiation. PVC must be kept away from naked flame. Improper storage can initiate degradation and colour change.

Health & Environment:

S6558 is not classified as a dangerous product. Dust and fines from the product may give a risk for dust explosion. All equipments should be properly grounded. Inhalation of dust may irritate the respiratory system and should be avoided. In case of formation of large amount of dust; close fitting safety clothing, safety goggles and breathing apparatus ,with particle filter according to DIN 3181, should be used.

Recycling:

Product is recyclable. It is recommended that product waste is recycled as much as possible. Dumping and land filling is also possible in agreement with the competent authorities.

Packaging:

This product is packed in 25 Kg paper bags.



LDPE	LLDPE	MDPE	HDPE	PP	PVC	GPPS	HIPS	EPS	PET	ABS	SBR	PBR	PC	EP
------	-------	------	------	----	-----	------	------	-----	-----	-----	-----	-----	----	----

PVC - S6558 POLYVINYL CHLORIDE

General Informations:

PVC contains approximately 56% by weight of chlorine. This polymer possesses thermoplastic properties. Grade S6558 has low porosity & high bulk density. Therefore it is most suitable for flexible applications.

Typical Specification:

Property	Unit	Value	Test Method
K-value	-	65	DIN- 53726
Sulphate ash	wt % max	0.05	DIN-53568/2
Volatiles	wt % max	0.2	ISO R-1269
Bulk density	gr/lit	600	DIN-53466
Screen analysis (residue on sieve) > 63 micron >250 micron	wt % min wt % max	90 5	DIN-53734 DIN-53734
Dark resin (particles in 250gr PVC)	No.max	30	HULS-6.7
Plasticizer acceptance	grDOP/100grPVC min.	10	DIN-53417/1
Fish eyes	number per 25 cm ² max.	5	HULS-6.9
Flowability (dia. of funnel outlet)	mm max.	4	HULS-6.10
Viscosity number	Cm ³ /gr	105	DIN- 53726
Residual VCM	ppm	≤1	HULS-6.11

The above data are typical laboratory average . They are intended to serve as guides only.