

FPC – Suspension PVC



Grade	Code	K value	Polymerization Degree	Bulk Density (g/c.c)	Volatile Matter (%)	Characteristic	Application
S-60	T	59.2~60.6	780±30	0.55±0.02	0.3↓	Suspension PVC with good gelling and very high transparency properties.	Used for extrusion, injection blow molding articles and calendering process of rigid film, sheet.
S-65S	F	64.6~66.0	1030±30	0.48±0.02	0.3↓	Suspension PVC with good plasticizer absorption and good heat stability.	Due to the excellent initial color prosperities especially used for transparent and white products.
S-65	F	64.6~66.0	1030±30	0.50±0.02	0.3↓	Suspension PVC with good plasticizer absorption and good heat stability.	This resin is intended for soft application, flexible film, and other flexible articles. It also suit for cables and wires application.
S-65	R	64.6~66.0	1030±30	0.53±0.02	0.3↓	Suspension PVC with good gelling properties,	Used for extrusion process of rigid pipe, large size rigid pipe.
S-65	D	65.7~67.1	1050±50	0.55±0.02	0.3↓	Suspension PVC with high bulk density, and excellent initial color prosperities	This resin is intended for rigid molding articles processing, particularly for extrusion process of rigid pipe with high extrusion quantity,

Test method : K Value : DIN 53726 Polymerization degree 、 Bulk Density 、 Volatile Matter : JIS-K6721

Code : T : Transparent F : Film R : Rigid D : High B.D