

Product Description

Polyvinyl Chloride Homopolymer having medium molecular weight, is white and free-flowing resins produced by suspension polymerization process. The resin can easily blend with variety of additives to achieve desired qualities needed in many applications. Applications are ranging from general purpose to special products regarding customer's satisfactions.

Typical Application

- Rigid Pipe, Door and Window Frames, Edge Band, Conduit, Other Rigid Profiles.

Product Characteristics

- High Bulk Density
- Good Flow ability

International Compliance

- REACH Compliance, EU
- Food Contact Applicable* (US FDA CFR177.1975, US)
- Not Contained of Specified Substances according to RoHS, EU

* This will legally not exempt the producers of final Food Contact articles to perform testing on their own products.

Physical Properties

Property	Test Method	Unit	Typical Value
K-Value	DIN 53726	-	66 *
Apparent Bulk Density	ISO - 60	g/ml	0.57
Volatile Matter	ISO - 1269	%	< 0.3
Sieve Analysis	ASTMD - 1921		
■ Retained on 250 micron		%	1
■ Retained on 75 micron		%	> 90
Impurity and Foreign Matter	ISO/R - 1265	Specks/100sq.	< 10

* corresponding Polymerization Degree = 1000

Processing Guidelines

PVC resin needs to be compounded with the properly additives by using standard mixing techniques. The optimum processing condition for each convertor depends on the formulation and the machine. Generally, the processing temperature is 120 to 170oC for soft products and 170 to 210oC for rigid products.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- White Powder

Product Packaging

- Paper Bag 25 Kilograms
- Flexy Bag 550 and 1,100 Kilograms
- Tank Car 10 and 20 Metric Tons
- Sea Bulk 17 Metric Tons