

SABIC® LDPE 7019EC

LOW DENSITY POLYETHYLENE FOR EXTRUSION COATING

DESCRIPTION

7019EC is a Low Density Polyethylene resin designed for mainly extrusion coating application. 7019EC contains no additives such as slipping agents or anti-blocking agents.

TYPICAL APPLICATIONS

Extrusion coating

TYPICAL PROPERTY VALUES

Revision 20210930

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190°C and 2.16kg	7.0	g/10 min	ISO 1133
Density			
Density	919	kg/m ³	ISO 1183
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile Properties			
Tensile Strength at Break	14	MPa	ASTM D638
Tensile Elongation at Break*	550	%	ASTM D638
Stiffness*	165	%	ASTM D746
ESCR	1.9	MPa	ASTM D1693
THERMAL PROPERTIES			
Vicat Softening Temperature			
Vicat Softening Temperature @10N	86	°C	ASTM D1525
Melting Point	106	°C	SABIC method

(1) Based on molded specimens.

PROCESSING CONDITIONS

Typical processing temperature: 300 - 340 °C.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical/medical applications.

STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.