

LF2103X



Low Density Polyethylene

Product Description

LF2103X is a low density homopolymer resin selected by customers for use in shrink packaging, bundling, pallet wrap and heavy-duty liner applications. LF2103X is also selected by customers for use in blow molding squeeze bottles and other specialty applications. Excellent bubble stability, melt strength, impact and shrinkage are key attributes of LF2103X. LF2103X contains an antioxidant.

Regulatory Status

For regulatory compliance information, see LF2103X [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Developmental
Availability	North America
Application	Agriculture Film; Bags & Pouches; Can Liners; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Liner Film; Shrink Film; Specialty Film; Textile Packaging Film
Market	Flexible Packaging
Processing Method	Blown Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.33	g/10 min	0.33	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.922	g/cm ³	0.922	g/cm ³	ASTM D1505
Product Density, (23 °C)	0.922	g/cm ³	0.922	g/cm ³	ASTM D1505
Film					
Dart Drop Impact Strength, F50	180	g	180	g	ASTM D1709
Tensile Strength at Break					
MD	4500	psi	31	MPa	ASTM D882
TD	4000	psi	28	MPa	ASTM D882
Tensile Elongation at Break					
MD	150	%	150	%	ASTM D882
TD	630	%	630	%	ASTM D882
1% Secant Modulus					
MD	32000	psi	220	MPa	ASTM D882
TD	43000	psi	296	MPa	ASTM D882
Elmendorf Tear Strength					
MD	190	g	190	g	ASTM D1922
TD	150	g	150	g	ASTM D1922
Optical					
Haze	15	%	15	%	ASTM D1003
Gloss	39		39		ASTM D2457
Additive					
Slip	None		None		LYB Method

Antiblock	None	None	LYB Method
-----------	------	------	------------

Notes

Data obtained from 2.0 mil (51 micron) film produced on a 2.5" blown film line with a 2.5:1 BUR, 0.030" die gap. These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.