



Formaldehyde Emissions TEST REPORT

EN 717-1:2004

For

Sofa

Model: JS series, YX series

Brand Name: J2S

Report No.: ENC2012255GZ25E1

Date of Issue: Jan. 4, 2021

Prepared For

Foshan J2S Furniture Co.,Ltd

**Floor 7, No.8, Anju Lane, Shafu Industrial Zone, Longjiang Town, Shunde
District, Foshan City, Guangdong**

Prepared By


East Notice Certification Service Co., Ltd.

**1/F, Haohui Commercial Building, Zhuji Street, Dongpu Town, Tianhe District,
Guangzhou City, China**

TEL: +86-20-8256 8534

FAX: +86-20-8256 8534

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ENC, this document cannot be reproduced except in full with our prior written permission. The document is available on request and the brief information for its validation can be assessable and confirmed at <http://www.enc-lab.com>.



1/F, Haohui Commercial Building, Zhuji Street,
Dongpu Town, Tianhe District, Guangzhou City

Tel:+86-020-8256 8534
E-mail: enc@enc-lab.com

Fax:+86-020-8256 8534
[Http:// www.enc-lab.com](http://www.enc-lab.com)

**GENERAL INFORMATION:**

Product Description:	Sofa
Model:	JS series, YX series
Model Difference:	The series models have same structure, except for the different appearance and size.
Brand:	J2S
Applicant:	Foshan J2S Furniture Co.,Ltd
	Floor 7, No.8, Anju Lane, Shafu Industrial Zone, Longjiang Town, Shunde District, Foshan City, Guangdong
Manufacturer:	Foshan J2S Furniture Co.,Ltd
	Floor 7, No.8, Anju Lane, Shafu Industrial Zone, Longjiang Town, Shunde District, Foshan City, Guangdong
Report No.:	ENC2012255GZ25E1
Test Methods:	EN 717-1:2004 Wood-based panels — Determination of formaldehyde release — Part 1: Formaldehyde emission by the chamber method. Limit mark: E1
Test Results:	Please refer to next page(s)
Sample Receiving Date:	Dec. 25, 2020
Test Performing Date:	Dec. 25, 2020 – Jan. 4, 2021

Should any objections to the test reports occurred, should submit it to the Company within ten days since the issuing of the report, Fail to accept.

The test results of this report relate only to the tested sample identified in this report.

Checked By

Yemig

Yemig Jan. 4, 2021

Authorized By

Ray Zhou

Ray Zhou Jan. 4, 2021

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ENC, this document cannot be reproduced except in full with our prior written permission. The document is available on request and the brief information for its validation can be assessable and confirmed at <http://www.enc-lab.com>.

East Notice Certification

1/F, Haohui Commercial Building, Zhuji Street,
Dongpu Town, Tianhe District, Guangzhou City

Tel:+86-020-8256 8534
E-mail: enc@enc-lab.com

Fax:+86-020-8256 8534
[Http:// www.enc-lab.com](http://www.enc-lab.com)

1 Description of the Applied Testing Method

The applied testing method complies with the test method according to EN 717-1. The test method is based on the published methods: ISO 16000-3, 16000-9, 16000-11. The internal method numbers are: 9810; 9811, 9812, 8400.

1.1 Test Specimen

The samples with the desired size were sent by the client to the laboratory of ENC in airtight packages. The packages were opened and edges were covered with tape according to EN 717-1. The specimens were transferred vertically into a test chamber immediately (internal method no.: 9810).

1.2 Test Chamber

The test chamber was consisting of stainless steel and had a volume of 119 litres. The air clean-up was realized in multiple steps. Before loading the chamber a blank check of the empty chamber was performed. The operation parameters were 23°C, 50 % relative air humidity (in the supply air) with an air exchange rate of 1 per hour. The total loading of the test chamber was 1 m² test specimens per m³ air volume (internal method 9811).

1.3 Sampling and Analysis

1.3.1 Testing of Formaldehyde

The presence of formaldehyde was tested by drawing air samples from the chamber outlet through DNPH-coated silicagel tubes. Analysis was done by solvent desorption, HPLC and UV-/diode array detection (ISO 16000-3, internal methods no.: 9812 / 8400).

The absence of formaldehyde was stated if the specific wavelength UV detector response was lacking at the specific retention time in the chromatogram. Otherwise it was checked whether the detection limit (0.003 mg/m³) was exceeded. In this case the identity was finally checked by comparing full scan sample UV spectra with full scan standard UV spectra. The uncertainty amounted to $\pm 20\%$ (RSD).

1.3.2 Deviations from EN 717-1

No deviations.

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ENC, this document cannot be reproduced except in full with our prior written permission. The document is available on request and the brief information for its validation can be assessable and confirmed at <http://www.enc-lab.com>.



2 Results

Wood Wool Acoustic Pane	Formaldehyde concentration in test chamber, mg/m ³
After 24 hours	0.040
After 48 hours	0.042
After 72 hours	0.044
After 96 hours	0.046
After 168 hours	0.046
After 192 hours	0.048
After 216 hours	0.049
After 240 hours	0.050

The results are average values of two samplings from the test chamber per day.

< less than

Steady-state Emission

With above data, following power function to determine the steady-state emission value was determined:

$$C = A/(1+Bt^D)$$

C= chamber concentration, mg/m³


T= time, h

The steady state emission was calculated with above formula at the time t= 240 h.

Sofa	Steady state emission, mg/m ³
Steady-state emission (240 h)	0.080

Steady state formaldehyde emission = 0.050mg/m³, Limit mark: E1

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ENC, this document cannot be reproduced except in full with our prior written permission. The document is available on request and the brief information for its validation can be assessable and confirmed at <http://www.enc-lab.com>.



APPENDIX

PHOTOGRAPH OF SAMPLE



---- END OF REPORT ----

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ENC, this document cannot be reproduced except in full with our prior written permission. The document is available on request and the brief information for its validation can be assessable and confirmed at <http://www.enc-lab.com>.