

TECHNICAL DATA SHEET

DURHARC MG 90

DESCRIPTION

Type of Product	Refractory Mortar
Main Component	Sintered Magnesia
Type of Bond	Ceramic
Type of Application	Trowelling

CHEMICAL COMPOSITION

MgO	90 %	ISO 12677
Fe ₂ O ₃	1,3 %	ISO 12677
CaO	2,5 %	ISO 12677
SiO ₂	5,5 %	ISO 12677

PHYSICAL PROPERTIES

Max. Service Temp.	1750 °C	
Partical Size	0-0,3 mm	ASTM C92

Date: 22 MAR. 2021 Revision: 0

The technical data shown are typical values. They can not be used as limits for a specification.
We reserve the right to change of product specifications.