



## TECHNICAL DATA

### DURHARC 40

**PRODUCT TYPE**

Maximum recommended temperature	: Alumina - Silica product
Main component	: Jointing material
Type of bond	: 1500°C
Appearance	: Chamotte
Installation method	: Ceramic
Maximum grain size	: Dry, for addition of water
Drinking water required for mixing on site	: Trowelling
	: 0.5 mm
	: 20.0 / 25.0 litres per 100 kg of dry material

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
<u>CHEMICAL ANALYSIS</u>			
Al2O3	ISO 12677	40.0	%
Fe2O3	ISO 12677	1.9	%
Na2O + K2O	ISO 12677	0.6	%

Commercial Code : MAM40048

Version : 10

Date : 05/10/2021

The data are current production averages. They cannot be used as limits for a specification.

CALDERYS AUSTRIA GmbH  
IZ-NO Süd Strasse 16, Objekt 69/7 Postfach 71 A-2355 Wiener Neudorf  
Tel:+43.2236.677090.0 - Fax:+43.2236.677093.11