



TECHNICAL DATA

DURHARC S 60

PRODUCT TYPE

	: Alumina product
	Jointing material
Maximum recommended temperature	: 1650°C
Main component	: Andalusite
Type of bond	: Ceramic
Appearance	: Dry, for addition of water
Installation method	: Trowelling
Maximum grain size	: 0.5 mm
Drinking water required for mixing on site	: 20.0 / 25.0 litres per 100 kg of dry material

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
<u>CHEMICAL ANALYSIS</u>			
Al ₂ O ₃	ISO 12677	58.0	%
Fe ₂ O ₃	ISO 12677	0.9	%
Na ₂ O + K ₂ O	ISO 12677	0.3	%

Commercial Code : MAM50026

Version : 10

Date : 16/08/2021

The data are current production averages. They cannot be used as limits for a specification.

CALDERYS AUSTRIA Gmbh
IZ-NO Süd Strasse 16, Objekt 69/7 Postfach 71 A-2355 Wiener Neudorf
Tel: +43.2236.677090.0 - Fax: +43.2236.677093.11