

PLICOTE D

Material:	High-elastic bitumen-sealing coating for mineral surfaces, resistant against most of diluted acids and alkalines.
Adherence:	On free of grease and frostfree, clean surfaces, free of colour, cement and separation materials.
Material needed:	approx. 500 ml/m ² / coating
Temperatur resistance:	-20°C up to +80°C
Working temperature:	+5°C up to +30°C
pH-value:	9
Density:	approx. 1,05 kg / litres (kg/dm ³)
Composition:	
Bitumen proportion:	approx. 72%
Water:	approx. 14%
Additional components (fillers):	approx. 14%
Packaging:	in 10 litre buckets
Storage:	cool and frostfree, the storage life is min. 12 months in closed original buckets.

Application:	The material can be layed on by gunning, painting or rolling. The installation is done directly from the bucket. If necessary it's possible to thin down PLICOTE D with water (max. 30%). PLICOTE in a fresh condition is water-soluble and sensitive to frost.
---------------------	--