



TECHNICAL DATA

CALDE® MAG GUN P 83

PRODUCT TYPE

	: Basic product
	Gunning mix
Maximum recommended temperature	: 1750°C
Main component	: Magnesia
Type of bond	: Chemical, Phosphate
Appearance	: Dry, for addition of water
Packaging	: Sacks or big bags
Shelf life	: 9 months
Installation method	: Gunning
Maximum grain size	: 3.5 mm
Material required	: 2.09 T/m ³
Drinking water required for mixing on site	: Added at the nozzle
Guidelines	: Installation Nr 26

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
<u>CHEMICAL ANALYSIS</u>			
MgO	EN ISO 1927-3	83.0	%
SiO ₂	EN ISO 1927-3	8.8	%
CaO	EN ISO 1927-3	3.9	%
Al ₂ O ₃	EN ISO 1927-3	0.6	%
Fe ₂ O ₃	EN ISO 1927-3	0.4	%

Commercial Code : MBG70015

Version : 12

Date : 18/08/2017

The data are current production averages. They cannot be used as limits for a specification.