

TECHNICAL DATA

CALDE® MIX FLASH A 55 MD

PRODUCT TYPE

	: Alumina - Silica product
	dry vibrating mix
Maximum recommended temperature	: 1650°C
Main component	: Andalusite , Chamotte
Type of bond	: Chemical - Inorganic
Appearance	: Dry, ready to use
Packaging	: Sacks
Shelf life	: packaging unit unopened : 12 months, packaging unit opened : 3 months
Installation method	: Dry vibration or ramming
Maximum grain size	: 3 mm
Guidelines	: Installation Nr 41 - Safety Nr 1

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
<u>CHEMICAL ANALYSIS</u>			
Al ₂ O ₃	EN ISO 1927-3	55.5	%
SiO ₂	EN ISO 1927-3	36.0	%
Fe ₂ O ₃	EN ISO 1927-3	1.0	%
<u>PHYSICAL PROPERTIES</u>			
<u>Measured on samples prepared according to</u>	EN ISO 1927-5		-
<u>Bulk density</u>			
after firing at 1200 °C	EN ISO 1927-6	2.12	g/cm ³
after firing at 1400 °C	EN ISO 1927-6	2.09	g/cm ³
<u>Cold crushing strength</u>			
after firing at 1200 °C	EN ISO 1927-6	10	MPa
after firing at 1400 °C	EN ISO 1927-6	15.6	MPa

Commercial Code : MAD50014

Version : 10

Date : 20/05/2022

The data are current production averages. They cannot be used as limits for a specification.