

GUNNING MASS for TUNDISH

General information

Classification	Slurry gunning mix
Main raw material components	Olivine, Sintered magnesia
Bonding type	Silicate bond
Grain Size	0-0.5 mm
Amount of Material	1,60 t/m ³
Storage Limit	12 months

Chemical analysis

MgO	CaO	SiO ₂	O Fe _{2 3}	O Al _{2 3}	
77,2%	2,4%	16,7%	2,6%	0,5%	
Determination on fired substance (1025 °C / 1877 °F) acc. to ISO 12677					

Physical properties

Poured Density	1,45 [g/cm ³]	EN 459-2
----------------	------------------------------	-------------