

## CALDE™ MIX M S 86 BTI

<b>PRODUCT TYPE</b>	: Basic product dry vibrating mix
Maximum recommended temperature	: 1700°C
Main component	: Magnesia
Type of bond	: Ceramic
Appearance	: Dry, ready to use
Packaging	: Sacks or big bags
Shelf life	: 6 months
Installation method	: Dry vibration or ramming
Maximum grain size	: 5 mm
Material required	: 2.80 T/m <sup>3</sup>
Guidelines	: Installation Nr 25a

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
<u>CHEMICAL ANALYSIS</u>			
MgO	EN 1402-3	84.0	%
Al <sub>2</sub> O <sub>3</sub>	EN 1402-3	12.0	%
SiO <sub>2</sub>	EN 1402-3	1.5	%

Commercial Code : MBD80026

Version : 11

Date : 09/01/2012

The data are current production averages. They cannot be used as limits for a specification.