

# TECHNICAL DATA

## CALDE® CAST NB 82 QD

### PRODUCT TYPE

	: Alumina - Silica product
	No cement castable
Maximum recommended temperature	: 1650°C
Main component	: Bauxite
Type of bond	: Mineral reaction
Appearance	: Dry, for addition of water
Packaging	: Sacks or big bags
Shelf life	: Sacks : 6 months - Big-Bags : 4 months
Installation method	: Vibrating
Maximum grain size	: 6 mm
Material required	: 2.75 T/m³
Drinking water required for mixing on site	: 6.0 / 7.0 litres per 100 kg of dry material
Guidelines	: Installation Nr 6-QD

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
<b>CHEMICAL ANALYSIS</b>			
Al <sub>2</sub> O <sub>3</sub>	EN ISO 1927-3	82.0	%
SiO <sub>2</sub>	EN ISO 1927-3	13.5	%
Fe <sub>2</sub> O <sub>3</sub>	EN ISO 1927-3	1.0	%
CaO	EN ISO 1927-3	0.2	%
<b>PHYSICAL PROPERTIES</b>			
<u>Measured on samples prepared according to</u>	EN ISO 1927-5		-
<u>Bulk density</u>			
after drying at 110 °C	EN ISO 1927-6	2.77	g/cm <sup>3</sup>
after firing at 800 °C	EN ISO 1927-6	2.76	g/cm <sup>3</sup>
<u>Cold crushing strength</u>			
after drying at 110 °C	EN ISO 1927-6	75	MPa
after firing at 800 °C	EN ISO 1927-6	80	MPa
after firing at 1200 °C	EN ISO 1927-6	150	MPa
after firing at 1400 °C	EN ISO 1927-6	110	MPa
<u>Permanent linear change</u>			
after firing at 800 °C	EN ISO 1927-6	-0.2	%
after firing at 1200 °C	EN ISO 1927-6	-0.3	%
after firing at 1400 °C	EN ISO 1927-6	+0.3	%
after firing at 1600 °C	EN ISO 1927-6	-0.2	%
<u>Thermal conductivity</u>			
at a mean temperature of 800 °C	EN ISO 1927-8	2.35	W/mK
at a mean temperature of 1000 °C	EN ISO 1927-8	2.26	W/mK
at a mean temperature of 1200 °C	EN ISO 1927-8	2.23	W/mK
<u>Abrasion resistance</u>			
after firing at 815°C	EN ISO 16282	< 6	cm <sup>3</sup>
<u>Reversible thermal expansion after firing.[20-1000 °C]</u>		0.76	%

Commercial Code : MAU70016

Version : 11

Date : 13/12/2013

The data are current production averages. They cannot be used as limits for a specification.