calderys
a member of Imerys

TECHNICAL DATA

CALDE® CAST HYMOR 2800

PRODUCT TYPE	: Alumina - Silica product Medium cement castable
Maximum recommended temperature	: 1480°C
Main component	: Chamotte
Type of bond	: Hydraulic
Appearence	: Dry, for addition of water
Packaging	: Sacks
Shelf life	: 6 months
Installation method	: Vibrating
Maximum grain size	: 6 mm
Material required	: 2.33 T/m³
Drinking water required for mixing on site	: 6.4 / 7.6 litres per 100 kg of dry material
Guidelines	: Installation Nr 6

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
CHEMICAL ANALYSIS			
Al2O3	EN ISO 1927-3	50.0	%
SiO2	EN ISO 1927-3	43.0	%
CaO	EN ISO 1927-3	4.2	%
Fe2O3	EN ISO 1927-3	0.8	%
PHYSICAL PROPERTIES			
Measured on samples prepared according to	EN ISO 1927-5	-	-
Bulk density			
after drying at 110 °C	EN ISO 1927-6	2.36	g/cm3
after firing at 800 °C	EN ISO 1927-6	2.27	g/cm3
Open porosity			
after firing at 800 °C	EN ISO 1927-6	20	%
Cold crushing strength			
after drying at 110 °C	EN ISO 1927-6	120	MPa
after firing at 800 °C	EN ISO 1927-6	115	MPa
after firing at 1200 °C	EN ISO 1927-6	85	MPa
after firing at 1400 °C	EN ISO 1927-6	90	MPa
Permanent linear change			
after firing at 800 °C	EN ISO 1927-6	-0.2	%
after firing at 1200 °C	EN ISO 1927-6	-0.3	%
after firing at 1400 °C	EN ISO 1927-6	-0.1	%
Thermal conductivity			
at a mean temperature of 800 °C	EN ISO 1927-8	1.37	W/mK
at a mean temperature of 1000 °C	EN ISO 1927-8	1.40	W/mK
at a mean temperature of 1200 °C	EN ISO 1927-8	1.44	W/mK
Abrasion resistance			
after firing at 815°C	EN ISO 16282	<7	cm3
Reversible thermal expansion after firing [20-1000 °C]		0.64	%

Commercial Code : MAF40057 Version : 11 Date : 06/11/2013

The data are current production averages. They cannot be used as limits for a specification.